

Rubber and Composite Hose Chemical Resistant Chart



Cedar Rapids, IA

Corporate Headquarters

Phone: 319.365.0471

Toll Free: 800.553.5455

Fax: 319.365.2522

Website: www.apache-inc.com



Chemical Resistance Information

This Apache document provides essential information that will facilitate the safe use of rubber and composite type chemical hoses.

Chemical hose users are cautioned that this Chemical Resistant has been developed from generally accepted industry standards. The ratings listed beneath each Elastomer are the base ratings for the chemical listed. This rating is based on the application temperature not exceeding 70°F (21.1°C) unless otherwise specified. The degree an Elastomer will resist the effects of a specific chemical depends on several variables. It is recommended that a hose with the highest resistant tube to the chemical transferred be used in the application for safety.

1. **Concentration** of the chemical is very significant (some chemicals may react with an Elastomer differently based on the level of concentration).
2. **Temperature** - as the temperature increases the deteriorative effect of a chemical may greatly increase on an Elastomer.
3. **Time** - the longer the duration the chemical is in contact with the Elastomer, the greater the deteriorative effect.
4. **Stability of the Chemical** - Chemical solutions (combining of different chemicals) may increase the deteriorative effect.
5. **Elastomer Grade** - There are different grades of specific Elastomer used in hose. The grade of Elastomer used may effect the resistance level of the hose to a specific chemical. It is recommended that only hose listed for chemical service be use.
6. **Safety**
 - a. Chemical hose tube must be inspected for discoloration, cracks or damage before each use in accordance with Apache "Proper Use, Care and Maintenance" booklet.
 - b. Never use damaged hose, remember all hose will fail in time! Err on the side of Safety, When in doubt about the condition of a hose, remove it from service!
 - c. Chemical hose should have the ends capped when not in use to keep out moisture and other elements that can cause chemical reactions.
 - d. Chemical hose should be cleaned after use to remove chemical residue.

These charts are offer as a guide only, when in doubt contact Apache for assistance. It is recommended that the hose user test the hose under all operating conditions to which the hose might be subjected to insure safe performance.

E - Excellent Resistance - suitable for continuous service - chemical may cause hose tube deterioration over time

G - Good Resistance - generally suitable for continuous service and intermittent service - chemical will cause hose tube deterioration over time.

C - Condition - suitable for intermittent service only - chemical will cause hose tube deterioration in a shorter time frame.

X - Not recommended

I - Insufficient data

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/ Fluorel)	Flurocarbon Plastic (Teflon/ TFE/FEP)	Modified Cross-link	UHMWP
Acetaldehyde	70	G	C	E	E	C	C	X	E	X	E	E	E
Acetamide	70	X	X	E	E	E	E	E	E	G	E	E	E
Acetic Acid (25%)	70	X	X	G	E	X	X	X	E	C	E	G	E
Acetic Acid (50%)	70	X	X	G	E	X	X	X	E	X	E	G	E
Acetic Acid Dilute	70	X	X	X	X	X	X	X	E	X	E	I	E
Acetic Acid,10%	70	G	G	G	E	G	G	C	E	C	E	G	E
Acetic Acid, 30%	70	G	G	G	E	G	G	C	E	C	E	I	E
Acetic Acid, 50%	70	C	C	G	G	G	G	X	E	C	E	G	E
Acetic Acid, Glacial	70	C	C	G	G	X	C	X	E	X	E	G	E
Acetic Aldehyde	70	I	I	I	I	I	I	I	I	I	I	I	E
Acetic Anhydride	70	G	C	G	G	G	E	X	E	X	E	G	E
Acetic Anhydride, 50 %	70	I	I	I	I	I	I	I	I	I	I	I	E
Acetone	70	C	C	E	E	C	G	X	E	X	E	G	E
Acetone Cyanohydrin	70	G	X	G	G	X	X	X	E	X	E	E	E
Acetonitrile	70	G	E	G	G	E	G	X	I	I	E	E	E
Acetophenone	70	C	X	E	E	X	X	X	G	X	E	G	G
Acetyl Acetone	70	I	I	I	I	I	I	X	E	X	E	E	E
Acetyl Chloride	100	X	X	C	C	X	X	X	G	X	E	C	X
Acetylene	70	G	G	E	E	G	G	E	E	E	E	E	E
Acetylene Dichloride	100	X	X	X	X	X	X	X	E	E	E	X	G
Acid Crude Tar	70	I	I	I	I	I	I	I	I	I	I	I	E
Acrolein (Inhibited)	70	I	I	I	I	I	I	I	I	I	I	E	I
Acrylic Acid	70	I	I	I	I	I	I	I	I	I	I	I	G
Acrylonitrile	100	X	X	I	X	X	C	X	G	E	E	G	G
Adipic Acid	70	E	E	G	E	G	I	E	I	I	I	I	I
Aero Safe 2300	70	I	I	I	I	I	I	I	I	I	I	E	I
Aeroshell 7A,17 Grease	70	I	I	I	I	I	I	I	I	I	I	X	I
Aeroshell 1A, 1AC,4	70	I	I	I	I	I	I	I	I	I	I	E	I
Agricultural Spray	70	X	X	C	G	C	C	C	E	G	E	G	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Air 180 F	70	X	E	E	E	E	E	E	X	E	E	E	E
Air 200 F	70	X	C	E	E	G	X	G	X	E	E	E	E
Air, Ambeint	70	E	E	E	E	E	E	E	E	E	E	E	E
Aircraft Hyd Oil AA	70	X	X	X	X	G	X	G	G	G	E	E	G
Alkazene (dibromoethyl-benzene)	70	X	X	X	X	X	X	X	I	G	I	X	I
Alkylaryl Sulfonates	70	I	I	I	I	I	I	I	I	I	I	E	I
Allyl Alcohol	70	E	E	E	E	E	E	E	E	G	E	I	E
Allyl Bromide	70	X	X	X	I	X	X	X	G	G	E	I	E
Allyl Chloride	70	X	X	I	X	X	X	X	E	G	E	E	E
Alum	150	E	E	I	E	E	E	E	E	E	E	I	E
Aluminum Acetate	100	X	E	I	E	E	E	E	E	X	E	E	E
Aluminum Bromide	70	E	E	E	E	E	E	E	I	E	E	E	I
Aluminum Chloride	150	E	E	I	E	E	E	E	E	E	E	E	E
Aluminum Fluoride	70	F	E	E	E	E	E	E	E	E	E	E	E
Aluminum Hydroxide	70	E	G	E	E	E	G	G	E	C	E	E	I
Aluminum Nitrate	70	E	E	E	E	E	E	E	E	G	E	E	E
Aluminum Phosphate	70	E	E	E	E	E	E	E	E	E	E	I	E
Aluminum Salts	70	I	I	I	I	I	I	I	I	I	I	E	E
Aluminum Sulfate	70	E	E	E	E	E	E	E	E	E	E	E	E
Alums (ammonium or potassium)	70	I	I	I	I	I	I	I	I	I	I	E	I
Amines (mixed)	70	I	I	I	I	I	I	I	I	I	E	C	I
Amino Ethanol	70	I	I	I	I	I	I	I	I	I	I	I	E
Aminoethylethanoiamine	70	I	I	I	I	I	I	I	I	I	I	I	E
Ammonia (aqueous)	70	X	X	X	X	X	X	X	I	I	I	E	E
Ammonia Cupric Sulfate	150	X	E	I	E	E	E	E	E	E	E	E	E
Ammonia Gas (cold)	70	E	E	E	E	E	E	E	E	X	E	I	E
Ammonia Gas (hot)	70	X	X	G	G	G	G	X	E	X	E	I	E
Ammonia Liquor	70	I	I	I	I	I	I	I	I	I	I	I	E
Ammonia Vapor	70	I	I	I	I	I	I	I	I	I	I	I	E
Ammonia Water	70	G	G	E	E	G	G	G	E	G	E	E	E
Ammonium Acetate	70	E	I	G	E	G	G	C	I	X	E	E	I
Ammonium Bicarbonate	70	E	E	E	E	E	E	E	I	E	E	I	I
Ammonium Bisufate (50%)	70	I	I	I	I	I	I	I	I	I	I	E	I
Ammonium Carbonate	70	E	E	E	G	G	I	X	E	E	E	E	E
Ammonium Chloride	150	E	E	I	E	E	E	E	E	E	E	E	E
Ammonium Dichromate	70	E	I	I	I	E	I	I	I	I	E	I	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Ammonium Hydroxide	150	E	X	I	X	E	G	X	E	X	E	E	E
Ammonium Metaphosphate	70	I	I	I	I	I	I	I	I	I	E	E	E
Ammonium Nitrate	150	G	X	I	E	G	E	E	E	I	E	E	E
Ammonium Nitrite	70	C	C	E	E	E	E	C	E	I	E	E	E
Ammonium Persulfate	70	E	X	G	G	G	E	X	E	I	E	G	E
Ammonium Phosphate	150	E	X	I	E	E	E	E	E	E	E	E	E
Ammonium Sulfare	70	E	G	E	E	E	E	X	E	E	E	E	E
Ammonium Sulfate	150	E	E	I	E	E	E	X	E	E	E	E	E
Ammonium Sulfide	70	E	C	E	E	E	E	E	E	C	E	E	E
Ammonium Sulfite	150	E	X	I	E	X	E	E	E	E	E	E	E
Ammonium Thiocyanate	70	E	X	E	E	X	E	E	E	E	E	E	E
Ammonium Thiosulfate	70	E	E	E	E	E	E	E	E	E	E	E	I
Amyl Acetate	70	X	X	G	G	X	X	X	E	X	E	E	E
Amyl Acid Phosphate	70	X	I	X	I	X	I	I	I	I	E	I	I
Amyl Alcohol	70	G	G	E	E	E	E	G	E	E	E	E	E
Amyl Amine	70	X	X	C	X	X	X	X	E	X	E	I	E
Amyl Borate	70	X	X	X	X	E	E	G	I	E	E	E	I
Amyl Bromide	70	X	X	X	X	X	X	X	I	E	E	I	I
Amyl Chloride	70	X	X	X	X	X	X	X	E	G	E	E	E
Amyl Chloronaphthalene	70	X	X	X	X	X	X	X	I	E	E	E	I
Amyl Ether	70	X	X	X	X	X	X	E	I	I	E	I	I
Amyl Iodide	70	X	X	X	X	X	X	X	I	I	E	I	I
Amyl Napthalene	70	X	X	X	X	X	X	X	G	E	E	E	I
Amyl Oleate	100	X	X	X	X	X	X	C	I	I	E	I	E
Amyl Phenol	100	X	X	X	X	X	X	X	E	E	E	G	E
Amyl Phthalate	100	X	X	I	X	X	X	X	E	X	E	I	E
Amylene	70	X	X	X	X	X	X	C	I	E	E	I	I
Anethole	100	X	X	X	X	X	X	X	X	C	E	X	X
Anhydrous Ammonia	Use hose only approved for NH3 Anhydrous Ammonia												
Aniline	70	G	G	E	E	X	X	X	E	G	E	G	E
Aniline Dyes	70	G	G	G	E	G	G	C	E	G	E	E	E
Aniline Hydro-Chloride	70	E	X	E	E	X	X	E	I	E	E	E	I
Aniline Oil	70	G	G	E	E	X	X	X	E	G	E	G	E
Animal Fats	70	X	X	G	E	G	G	E	E	E	E	E	E
Animal Gelatin	100	X	X	X	X	G	E	E	E	E	E	E	E
Animal Grease	100	X	X	X	X	G	E	E	E	E	E	G	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Animal Oils	100	X	X	X	X	G	E	E	E	E	E	G	E
Ansul Ether	70	X	X	C	C	X	X	C	E	X	I	I	E
Antifreeze (glycol base)	70	E	E	E	E	E	E	E	E	E	E	E	E
Anitimony Chloride	70	I	I	I	I	I	I	I	I	I	E	E	I
Antimony Chloride (50%)	70	I	I	I	I	I	I	I	I	I	E	I	E
Antimony Salts	70	I	I	I	I	I	I	I	I	I	E	E	I
Antimony Trichloride	70	I	I	E	E	I	I	G	E	E	E	I	E
Aqua Ammonia	70	X	X	I	I	I	I	I	I	I	E	I	E
Aqua Regia	70	X	X	X	C	X	C	X	C	C	E	C	C
Arco ATF Dexron	70	I	I	I	I	I	I	I	I	I	I	E	I
Arco C2, 1000	70	I	I	I	I	I	I	I	I	I	I	E	I
Aroclor 1248	70	X	X	C	C	X	C	C	I	E	I	I	I
Aroclor 1254	70	X	X	X	C	X	X	X	I	E	I	I	I
Aroclor 1260	70	E	E	E	E	E	E	E	I	E	I	I	
Aroclor, Monsanto	70	I	I	I	I	I	I	I	I	I	I	I	I
Aromatic Hydrocarbons	100	X	X	X	X	X	X	X	E	E	E	X	E
Aromatic Spirits	100	X	X	X	X	X	X	X	E	E	E	X	E
Aromatic Tar	100	X	X	X	X	X	X	X	E	E	E	I	E
Arquads	70	E	E	I	E	E	E	E	E	E	E	E	E
Arsenic Acid	100	G	E	I	E	E	E	E	E	X	E	E	E
Arsenic Salts	70	I	I	I	I	I	I	I	I	I	I	X	I
Arsenic Trichloride	100	X	X	X	X	X	X	X	X	X	X	I	I
Askarel	70	X	X	X	X	X	X	G	G	E	I	G	I
Asphalt	70	X	X	X	X	G	C	G	X	E	E	G	X
Asphalt (180 F & above)	180	Use only Host Asphalt Hose											
ASTM Fuel A	70	X	X	X	X	E	E	E	E	E	E	E	G
ASTM Fuel B	70	X	X	X	X	C	X	G	E	E	E	G	G
ASTM Fuel C	70	X	X	X	X	X	X	G		E	E	G	E
ASTM Oil No. 1	100	X	X	X	X	E	G	E	E	E	E	E	E
ASTM Oil No. 2	100	X	X	X	X	G	C	E	E	E	E	E	E
ASTM Oil No. 3	100	X	X	X	X	G	C	E	E	E	E	E	E
ATF Special Auto Trans. Fluid	70	I	I	I	I	I	I	I	I	I	E	E	I
Automatic Brake Fluid	70	I	I	I	I	I	I	I	I	I	E	I	I
Baking Soda (Sodium Bicarb)	70	E	E	E	E	E	E	E	E	E	E	I	E
Baltic Types	70	I	I	I	I	I	I	I	I	I	I	E	I
Banana Oil (Amyl-Acetate)	70	X	X	G	G	X	X	X	E	X	E	I	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Blast Furnace Gas	70	C	C	C	C	G	G	C	E	E	E	E	E
Bleach	100	X	X	X	E	X	X	X	X	X	E	C	X
Bleach Solutions	70	X	X	X	E	X	X	X	X	X	E	C	X
Blue Vitriol (Copper Sulfate)	70	E	E	E	E	E	E	E	E	E	E	I	E
Borax (Sodium Teraborate)	70	E	E	E	E	E	E	E	E	E	E	E	E
Bordeau Mixture	70	E	E	E	E	E	E	E	E	E	E	E	E
Boric Acid	70	E	E	E	E	E	E	E	E	E	E	E	E
Boric Copper Sulfate	70	I	I	I	I	I	I	I	I	I	E	G	I
Brake Fluid-Petroleum base	70	I	I	I	I	I	I	I	I	I	E	E	I
Brake Fluid - Synthetic base	70	I	I	I	I	I	I	I	I	I	E	E	I
Brine	70	E	E	E	E	E	E	E	E	E	E	E	E
Brine (Sodium Chloride Solution)	70	E	E	E	E	E	E	E	E	E	E	E	E
Bromine	100	X	X	X	X	X	X	X	X	B	E	I	X
Bromine Trifluoride	70	X	X	X	X	X	X	X	X	X	X	I	X
Bromine Water	70	X	X	C	C	C	G	X	I	E	E	I	I
Bromine-Anhydrous	70	X	X	X	X	X	X	X	X	E	E	I	X
Bromobenzene	70	X	X	X	X	X	X	X	G	E	E	I	X
Bromochloromethane	70	X	X	G	C	E	E	E	C	G	E	I	G
Bromotoluene	70	I	I	I	I	I	I	I	I	I	I	I	X
Bunker C	100	X	X	X	X	C	X	X	X	E	E	G	E
Bunker Oil	100	X	X	I	X	C	X	E	E	E	E	G	E
Butadiene	70	X	X	C	C	C	G	C	E	G	E	E	E
Butane	Use only hose approved for Butane service												
Butane (Liquid)	Use only hose approved for Butane service												
Butanol (Butyl Alcohol)	100	X	X	I	E	E	E	G	E	C	E	E	E
Butter	100	X	X	X	X	G	G	E	E	X	E	X	E
Butter Oil (Use FDA Hose)	100	I	I	I	I	I	I	E	E	I	E	I	E
Butyric Acid	70	I	I	I	I	I	I	I	I	I	E	I	I
Butyl Acetoacetate	70	I	I	I	I	I	I	I	I	I	E	I	E
Butyl Aceryl Ricinoleate	70	X	X	E	E	C	C	C	I	E	E	I	I
Butyl Acrylate	100	X	X	X	X	X	X	X	G	X	E	I	G
Butyl Alcohol	100	X	X	I	E	E	E	G	E	C	E	E	E
Butly Alcohol Secondary	70	I	I	I	I	I	I	I	I	I	E	I	E
Butyl Aldehyde	70	X	X	G	G	G	C	X	E	X	E	I	E
Butyl Amine	70	X	X	C	C	X	X	C	E	X	E	E	E
Butyl Benzene	100	X	X	X	X	X	X	X	E	E	E	C	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Butyl Benzoate	70	X	C	E	E	X	X	X	I	E	E	I	I
Butyl Benzyl Phthalate	100	X	X	I	X	X	XX	X	E	X	E	I	E
Butyl Bromide	100	X	X	X	X	X	X	X	G	G	E	G	G
Butyl Butyrate	100	X	X	X	X	X	X	X	G	X	E	I	G
Butyl Carbitol	70	X	X	E	E	G	E	C	E	E	E	E	E
Butyl Cellosolve	70	X	X	E	E	C	G	C	E	X	E	I	E
Butyl Ether	70	X	X	G	C	C	C	C	E	X	E	E	E
Butyl Ethyl Acetaldehyde	100	X	X	X	X	X	X	X	E	X	E	G	E
Butyl Ethyl Ether	100	X	X	X	X	X	X	X	E	I	E	E	E
Butyl Formate	70	X	X	I	I	X	X	X	I	I	E	I	I
Butyl Iodide	70	X	X	I	I	X	I	X	I	I	E	I	I
Butyl Mercaptan (Tertiary)	70	I	I	I	I	I	I	I	I	I	E	E	I
Butyl Oleate	70	X	X	G	G	X	X	X	I	E	I	I	I
Butyl Phthalate	70	X	X	E	I	I	X	X	E	C	E	I	E
Butyl Stearate	70	X	X	C	C	X	X	G	E	E	E	E	E
Butyl -Acetate	70	X	X	G	G	X	C	X	E	X	E	G	E
Butylene	70	X	X	X	X	C	C	G	I	E	E	I	I
Butyraldehyde	70	X	X	G	G	C	X	X	E	X	E	G	E
Butyric Acid	70	E	X	E	E	C	C	X	E	G	E	I	E
Butyronitrile	70	X	X	E	E	X	I	X	I	I	E	I	I
Cadmium Acetate	70	I	I	I	I	I	I	I	I	I	E	I	E
Cadmium Salts	70	I	I	I	I	I	I	I	I	I	E	I	E
Cake Alum (Aluminum Sulfate)	70	E	E	E	E	E	E	E	E	E	E	E	E
Calcine Liquor	70	I	I	I	I	I	I	I	I	I	E	E	I
Calcium Acetate	100	X	X	I	E	I	E	X	E	X	E	E	E
Calcium Aluminate	70	I	I	I	I	I	I	I	I	I	E	I	E
Calcium Arsenate	70	I	I	I	I	I	I	I	I	I	I	G	I
Calcium Bichromate	150	X	X	I	X	X	X	X	X	X	E	X	X
Calcium Bisulfate	150	E	I	I	E	E	E	E	E	E	E	E	E
Calcium Bisulfide	150	I	I	I	E	I	I	E	I	E	E	E	E
Calcium Bisulfite	70	X	X	I	X	E	E	E	E	E	E	E	E
Calcium Carbonate	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Chlorate	70	I	I	I	I	I	I	I	I	I	E	E	I
Calcium Chloride	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Hydroxide	100	E	E	I	E	E	C	C	E	X	E	E	E
Calcium Hypochlorate	100	X	X	I	X	X	I	X	X	X	E	E	G

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Calcium Hypochlorite	70	C	X	E	E	X	E	C	E	E	E	E	G
Calcium Nitrate	150	E	I	I	E	I	E	G	E	E	E	I	E
Calcium Nitrite	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Salt	70	I	I	I	I	I	I	I	I	I	E	I	E
Calcium Silicate	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Sulfate	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Sulphhydrate	100	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Sulfide	150	E	I	I	E	I	E	E	E	E	E	E	E
Calcium Sulfite	150	E	I	I	E	I	E	E	E	E	E	E	E
Caliche Liquors	70	I	I	I	I	I	I	I	I	I	E	E	E
Cane Sugar Liquors	70	E	E	E	E	E	E	E	E	E	E	E	E
Caprylic Acid	100	X	X	X	X	X	X	X	E	I	E	E	E
Carbamate	70	X	X	G	G	G	G	C	I	E	E	E	I
Carbitol	100	X	I	I	E	I	E	X	E	E	E	E	E
Carbitol Acetate	100	X	X	X	X	X	X	X	E	I	E	E	E
Carbolic Acid (Phenol)	100	X	I	I	X	I	I	I	I	I	E	C	E
Carbolic Acid	70	X	I	E	X	I	E	I	I	I	E	C	E
Carbon Bisulfide	70	X	X	X	X	X	X	G	I	E	E	I	I
Carbon Dioxide	100	E	I	I	E	I	E	E	E	E	E	E	E
Carbon Dioxide (Wet)	70	I	I	I	I	I	I	I	I	I	E	E	I
Carbon Disulfide	70	X	X	X	X	X	X	X	X	E	E	X	X
Carbon Monoxide	70	E	E	E	E	E	E	E	E	E	E	E	E
Carbon Terrachloride	100	X	X	X	X	X	X	X	E	E	E	C	G
Carbon Terrafluoride	70	I	I	E	E	I	I	I	I	I	E	I	I
Carbonic Acid	100	E	I	I	E	I	E	E	E	E	E	E	E
Caro Syrup	100	I	I	I	I	I	I	I	E	I	E	I	E
Casein	70	I	I	I	I	I	I	I	I	I	E	E	I
Casing Head Gasoline	70	I	I	I	I	I	I	I	I	I	E	I	G
Castor Oil	100	X	I	I	E	I	E	E	E	E	E	E	E
Caustic	70	I	I	I	I	I	I	I	I	I	E	I	E
Caustic Potash	70	G	G	E	E	G	E	G	E	G	E	E	E
Caustic Soda	150	E	I	I	E	I	C	C	E	X	E	E	E
Caustic Soda (20%)	70	I	I	I	I	I	I	I	I	I	E	G	E
Ceilugard , 200	70	I	I	I	I	I	I	I	I	I	E	E	I
Ceilulube,1000,220AST220,A60	70	I	I	I	I	I	I	I	I	I	E	E	I
Cellosize	100	X	X	I	X	X	X	X	E	I	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Cellosolve	100	X	I	I	I	I	X	X	E	I	E	E	E
Cellosolve Acetate	100	X	I	I	I	I	X	X	E	I	E	E	E
Cellosolve, Butyl (under 100 F)	70	I	I	I	I	I	I	I	I	I	E	G	E
Cellulube	70	X	X	E	E	X	X	X	E	E	E	E	E
China Wood Oil (Tung Oil)	70	X	X	C	C	E	G	E	E	E	E	E	E
Chlordane	70	I	I	I	I	I	I	I	I	I	I	E	E
Chlorinated Solvents	100	X	X	X	X	X	X	X	E	E	E	I	G
Chlorine (Dry)	70	No hose recommended											
Chlorine (Wet)	70	X	X	X	X	X	X	X	C	C	E	X	X
Chlorine 3% solution	70	X	X	X	I	X	X	X	X	E	E	I	E
Chlorine Dioxide	70	X	X	C	C	X	G	X	I	E	I	I	I
Chlorine Saturated Solution	70	X	X	X	I	X	G	C	I	E	E	I	I
Chlorine Trifluoride	70	X	X	X	X	X	X	X	I	X	X	X	I
Chlorine Water	70	I	I	I	I	I	I	I	I	I	E	E	I
Chloroacetic Acid	70	X	X	C	C	X	G	X	E	X	E	E	E
Chloroacetone	70	X	X	G	E	C	C	X	E	X	E	I	E
Chloroacetonitrile	70	C	I	C	I	C	I	C	I	I	I	I	I
Chlorobenzene	70	X	X	X	X	X	X	X	E	E	E	G	G
Chlorobenzol	100	X	X	X	X	X	X	X	X	E	E	C	E
Chlorobromomethane	70	X	X	E	E	X	X	X	E	E	E	G	E
Chlorobutadiene	70	X	X	X	X	X	X	X	I	E	I	I	I
Chlorobutane	100	X	X	X	X	X	X	X	I	E	E	I	X
Chlorododecane	70	X	X	X	X	X	X	X	I	E	I	I	I
Chloroethyl Benzene	70	X	X	X	X	X	X	X	G	G	E	I	G
Chloroform (Trichloromethane)	70	X	X	X	X	X	X	X	G	E	E	G	G
Chloronaphthalene	70	X	X	X	X	X	X	X	I	E	E	I	I
Chloropentane	100	X	X	X	X	X	X	X	X	E	E	I	E
Chlorophenol	100	X	X	X	X	X	X	X	X	E	E	C	E
Chloropropane	100	X	I	X	X	X	X	X	X	X	E	I	E
Chlorosulfonic Acid	100	X	X	X	X	X	X	X	X	X	E	I	X
Chlorothene	70	X	X	X	X	X	X	X	E	E	E	I	E
Chlorotoluene	70	X	X	X	X	X	X	X	E	E	E	X	E
Chlorox (Sodium Hypochlorite)	70	X	X	G	G	G	E	G	E	E	E	G	E
Chocolate Syrup	100	I	I	I	E	E	I	E	E	I	E	G	E
Chrome Alum	70	I	I	I	I	I	I	I	I	I	E	E	E
Chrome Plating Solutions	70	X	X	G	G	X	X	X	I	E	E	I	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Chromic Acid	70	X	X	C	C	X	E	X	E	E	E	E	E
Chromic Acid (100%)	70	X	X	X	X	X	X	X	X	X	E	X	E
Chromic Acid (25%)	100	X	X	X	X	X	X	X	X	I	E	C	E
Chromic Acid (50%)	70	I	I	I	I	I	I	I	I	I	E	X	E
Chromium Salts	70	I	I	I	I	I	I	I	I	I	E	G	I
Cider	100	I	I	I	E	E	I	E	I	I	E	I	E
Citgo FR Fluids	70	I	I	I	I	I	I	I	I	I	E	E	E
Citric Acid	70	E	G	E	E	E	E	G	E	E	E	E	E
Citrous Oils	70	X	X	F	G	X	X	C	I	I	E	I	E
Coal Gas	70	I	I	I	I	I	I	I	I	I	E	E	I
Coal Oil	70	I	I	I	I	I	I	I	I	I	E	I	E
Coal Tar (Creosote)	70	X	X	X	X	G	C	E	G	E	E	X	G
Coal Tar (Naptha)	70	I	I	I	I	I	I	I	E	E	E	C	E
Cobalt Chloride	70	E	E	E	E	E	E	E	E	E	E	E	E
Cobalt Chloride	100	I	I	I	I	I	I	I	E	I	E	E	E
Coconut Oils	70	X	X	C	C	G	C	E	E	E	E	I	E
Cod Liver Oil	70	X	X	E	E	G	G	E	E	E	E	E	E
Coke Oven Gas	70	X	X	X	X	X	G	X	E	E	E	E	E
Cologne Spirits (Ethyl Alcohol)	70	E	E	E	E	E	E	E	E	E	E	I	E
Copper Acetate	70	E	X	E	E	E	G	E	I	X	E	I	I
Copper Arsenate (Cupric Arsenate)	70	I	I	I	I	I	I	I	I	I	E	E	E
Copper Chloride	100	X	I	I	E	I	E	E	E	E	E	E	E
Copper Cyanide	70	E	E	E	E	G	G	E	E	E	E	E	E
Copper Hydrate	100	X	E	I	I	I	I	C	E	X	E	E	E
Copper Hydroxide	100	X	X	I	I	I	C	C	E	X	E	E	E
Copper Nitrate	100	X	I	I	E	I	E	E	E	E	E	E	E
Copper Nitrate (Cupric Nitrate)	70	I	I	I	I	I	I	I	I	I	E	I	I
Copper Nitrite	100	X	I	I	E	I	E	E	E	E	E	E	E
Copper Sulfate	70	E	E	E	E	E	E	E	E	E	E	E	E
Copper Sulfide	100	X	I	I	E	I	E	E	E	E	E	E	E
Corn Oil	70	X	X	I	C	C	G	E	E	E	E	E	E
Corn Syrup	100	I	I	I	I	I	I	G	E	I	E	E	E
Cottonseed Oil	70	X	X	I	G	G	G	E	E	E	E	E	E
Creosote	100	X	X	X	X	X	X	F	G	E	E	G	E
Cresols	100	X	X	X	X	C	C	C	E	E	E	G	E
Cresylic Acid	70	X	X	X	X	X	C	C	E	E	E	I	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Crotonaldehyde	70	I	I	I	I	I	I	I	I	I	E	I	E
Crude Oil	70	X	X	X	X	X	X	E	E	E	E	C	E
Crude Petroleum Oil	70	X	X	X	X	X	X	E	E	E	E	C	E
Crude Wax	70	X	X	X	X	X	X	E	E	E	E	C	E
Cryolite	70	I	I	I	I	I	I	I	I	I	I	G	I
Cumene	100	X	X	X	X	X	X	X	E	E	E	G	E
Cupric Carbonate	100	X	X	X	E	I	E	E	E	E	E	E	E
Cupric Chloride	70	G	E	E	E	G	E	E	E	E	E	I	E
Cupric Hydroxide	70	C	G	E	I	I	G	G	E	C	E	I	E
Cupric Nitrate	100	X	I	I	E	I	E	E	E	E	E	E	E
Cupric Nitrite	100	X	I	I	E	I	E	E	E	E	E	E	E
Cupric Sulfate	100	X	I	I	E	E	E	E	E	E	E	I	E
Cutting Fluid (Oil)	70	X	X	X	X	G	G	E	E	E	E	G	E
Cutting Oil, Sulfur Base	70	I	I	I	I	I	I	C	I	I	E	I	E
Cutting Oil, Water Soluble	70	I	I	I	I	I	I	E	I	I	E	X	E
Cyclohexane	70	X	X	X	X	E	X	E	E	E	E	E	E
Cyclohexanol	70	C	X	X	C	E	G	C	E	E	E	G	E
Cyclohexanone	70	X	X	C	C	X	X	X	E	X	E	E	E
Cyclopentane	100	X	X	X	X	I	C	C	E	E	E	C	E
Cyclopentanol	100	X	X	X	X	X	X	C	E	I	E	E	E
Cyclopentanone	70	X	X	X	X	X	X	X	E	X	E	C	E
Dasco FR150,FR200,FR200BFR310	70	I	I	I	I	I	I	I	I	I	E	E	E
Dasco FRD200,DC510,DC550,DC560	70	I	I	I	I	I	I	I	I	I	E	E	E
DDT in Kerosene	70	X	X	X	X	C	X	E	E	E	E	I	E
Decalin (Decahydronaphthalene)	70	X	X	X	X	X	X	X	E	E	E	E	G
Decane	100	X	X	X	X	X	X	X	X	E	E	X	X
Decanol	100	X	I	X	E	I	E	E	E	X	E	E	E
Dectol R & O Oils	70	I	I	I	I	I	I	I	I	I	E	I	I
Decyl Alcohol	100	X	X	X	X	X	X	C	E	E	E	E	E
Decyl Aldehyde	100	X	X	X	X	X	X	X	E	X	E	C	E
Decyl Butyl Phthalate	100	X	X	X	X	X	X	X	E	X	E	C	E
Denatured Alcohol	70	E	E	E	E	E	E	E	E	G	E	E	E
Detergent Solutions	70	E	E	E	E	E	E	E	I	E	E	E	E
Developing Fluids	70	E	E	E	E	E	E	E	I	E	E	E	E
Dexron	70	I	I	I	I	I	I	I	I	I	I	X	I
Dextrin	70	I	I	I	I	I	I	I	I	I	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Fluorocarbon (Viton/Fluorel)	Fluorocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Diacetone	70	C	C	E	E	G	G	X	E	X	E	E	E
Diacetone Alcohol	70	C	C	E	E	G	G	X	E	X	E	E	E
Diamonium Phosphate	70	I	I	I	I	I	I	I	I	I	I	E	I
Diamyl Phenol	100	X	X	X	X	X	X	X	E	X	E	I	E
Diamylamine	100	X	X	E	X	X	X	X	E	I	E	C	E
Diamylene	100	X	X	X	X	X	X	X	E	E	E	C	E
Diazinon, Dilute	70	I	I	I	I	I	I	I	I	I	E	X	G
Dibenzyl Sebecate	70	X	X	G	G	X	X	X	I	G	E	I	I
Dibenzylether	70	X	X	G	G	X	X	X	E	X	E	E	E
Dibromobenzene	100	X	X	X	X	X	X	X	E	E	E	I	G
Dibromoethylbenzene	70	X	X	X	X	X	X	X	I	G	I	I	I
Dibutyl Acetate	70	I	I	I	I	X	I	I	E	I	E	I	E
Dibutyl Amine	100	X	X	X	X	X	X	X	I	X	E	I	E
Dibutyl Ether	100	X	X	C	X	X	X	X	E	C	E	E	E
Dibutyl Phthalate	100	X	X	E	X	X	X	X	E	X	E	E	E
Dibutyl Sebacate	70	X	X	G	G	X	X	X	E	G	E	E	E
Dicalcium Phosphate	100	E	I	I	E	I	E	E	E	E	E	E	E
Dichloroacetic Acid	100	X	X	X	X	X	X	X	E	X	E	I	E
Dichlorobutane	100	X	X	X	X	X	X	X	E	E	E	I	E
Dichloro-Difluoro Methane	70	G	G	G	G	E	E	E	I	G	I	I	I
Dichloroethane	70	X	X	C	I	X	X	X	E	E	E	I	E
Dichloroethyl Ether	100	X	X	X	X	X	X	X	E	X	E	C	E
Dichloroethylene	100	X	X	X	X	X	X	X	X	X	E	X	X
Dichloro-Fluoro Methane	70	X	X	X	X	X	X	X	E	X	I	I	E
Dichlorohexane	100	X	X	X	X	X	X	X	E	E	E	E	E
Dichloro-Isopropyl Ether	70	X	X	X	C	X	X	X	I	C	I	I	I
Dichloromethane	70	X	X	X	X	X	X	X	G	G	E	I	E
Dichloropentane	100	X	X	X	X	X	X	X	E	E	E	C	E
Dichloropropane	100	X	X	X	X	X	X	X	E	E	E	I	E
Dicyclohexylamine	70	X	X	X	X	X	X	C	G	X	E	I	G
Diesel Oil	70	X	X	X	X	G	G	E	E	E	E	I	E
Diethanolamine	70	G	G	E	I	I	C	G	E	E	E	E	E
Diethyl Benzene	70	X	X	X	X	X	X	X	E	E	E	I	G
Diethyl Carbinol	70	E	I	E	I	I	I	E	E	C	E	E	E
Diethyl Carbonate	70	X	X	X	X	X	X	X	E	E	E	I	E
Diethyl Ether	70	X	X	C	X	C	C	X	E	X	E	G	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Diethyl Ketone	70	X	X	G	G	X	X	X	E	X	E	I	E
Diethyl Oxalate	70	C	C	C	X	X	X	X	E	I	I	I	E
Diethyl Phthalate	70	X	X	E	I	I	X	X	E	C	E	E	E
Diethyl Sebcate	70	X	X	E	G	X	G	C	E	G	E	E	E
Diethyl Sulfate	100	X	X	X	X	X	X	X	E	X	E	E	E
Diethyl Triamine	100	X	I	E	I	I	X	C	E	I	E	E	E
Diethylamine	70	E	E	E	E	E	C	G	E	X	E	I	E
Diethylamine	100	I	I	E	I	I	I	X	E	I	E	I	E
Diethylbenzene	70	I	I	I	I	I	I	I	I	I	E	E	I
Diethylene Glycol	70	E	E	E	E	E	E	E	E	E	E	E	E
Diethylene Triamine	70	I	I	I	I	I	I	I	I	I	E	I	E
Dihydroxyethyl Amine	70	I	I	I	I	I	I	I	I	I	E	I	E
Dihydroxyethyl Ether	100	E	I	E	E	I	E	E	E	E	E	E	E
Diisobutyl Ketone	70	X	X	G	G	X	X	X	E	X	E	E	E
Diisobutylene	70	X	X	X	X	X	X	G	E	E	E	E	E
Diisooctyl Adipate	70	I	I	I	I	I	I	I	I	I	E	I	E
Diisocyanate	100	X	X	X	X	X	X	X	E	X	E	C	E
Diisodecyl Adipate	100	X	X	E	I	X	X	X	E	I	E	I	E
Diisodecyl Phthalate	100	X	X	E	X	X	X	X	E	I	E	I	E
Diisopropanyl Amine	100	X	X	E	X	X	X	X	E	I	E	C	E
Diisopropyl Amine	100	X	X	E	X	X	X	C	E	I	E	C	E
Diisopropyl Benzene	70	X	X	X	X	X	X	X	I	E	I	I	I
Diisopropyl Ether	70	X	X	X	X	X	X	G	E	I	E	I	E
Diisopropyl Ketone	70	X	X	E	E	X	X	X	E	X	E	E	E
Diisopropylidene Acetone	70	X	X	G	C	X	X	X	I	X	I	I	I
Dilauryl Ether	70	X	X	X	X	X	X	X	E	X	G	C	E
Dimehtylsulfate	70	X	X	X	X	X	X	X	E	I	C	C	E
Dimethylamine	70	G	G	E	I	I	X	G	E	I	E	I	E
Dimethyl Aniline	70	X	X	C	G	X	X	X	E	X	E	E	I
Dimethyl Benzene	100	X	X	X	X	X	X	X	E	E	E	C	E
Dimethyl Ether	70	X	X	C	X	C	G	E	E	E	I	E	I
Dimethyl Formamide	70	X	X	C	G	X	X	G	G	X	E	G	G
Dimethyl Phthalate	70	X	X	E	E	X	X	X	E	E	E	E	E
Dimethyl Sulfide	No hose recommended for this chemical												
Dimethylanoline	70	I	I	I	I	I	I	I	I	I	E	I	E
Dimethylketone	100	X	X	X	X	X	X	X	E	X	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Dimethyl Phenol	100	X	X	X	X	X	X	X	E	E	E	E	E
Dinitrobenzene	100	X	X	X	X	X	X	X	E	E	E	C	E
Dinitrotoluene	70	X	X	X	X	X	X	X	I	X	I	I	I
Diethyl Adipate	70	X	X	E	G	X	X	X	E	C	E	I	E
Diethyl Phthalate	70	X	X	E	G	X	X	X	E	C	E	E	E
Diethyl Sebacate	70	X	X	E	G	X	X	X	E	G	E	E	E
Diocyl Amine	100	X	X	X	X	X	X	X	E	C	E	C	E
Dioxane (Diethylene Ether)	100	X	X	E	X	X	X	X	E	X	E	E	E
Dioxocane	70	X	X	C	G	X	X	X	E	X	E	I	E
Dioxolane	100	X	X	X	X	X	X	X	E	I	E	C	E
Dipentene	70	X	X	X	X	X	X	G	E	E	E	E	E
Diphenyl (Phenylbenzene)	70	X	X	X	X	X	X	X	I	E	E	I	I
Diphenyl Oxides	70	X	X	X	X	X	X	X	I	E	E	I	I
Diphenyl Phthalate	100	X	X	I	X	X	X	X	E	X	E	E	E
Dipropyl Ketone	100	X	X	X	X	X	X	X	E	X	E	E	E
Dipropylamine	100	X	X	E	X	X	X	X	E	C	E	E	E
Dipropylene Glycol	100	E	I	E	E	I	E	E	E	E	E	E	E
Dirco Oils	70	I	I	I	I	I	I	I	I	I	E	E	E
Disodium Phosphate	70	E	E	E	I	I	E	E	E	I	E	I	E
Divinyl Benzene	70	X	X	X	I	I	X	X	E	E	E	I	E
Dodecyl Benzene	100	X	X	X	X	X	X	X	E	I	E	C	E
Dodecyl Toluene	100	X	X	X	X	X	X	X	E	E	E	C	E
Dow-Pet	100	X	X	X	X	X	X	X	E	E	E	C	E
Dowtheerm A	100	X	X	X	X	X	C	X	E	E	E	E	E
Dowtherm E	100	X	X	X	X	X	C	X	E	E	E	E	E
Dowtherm Oil	70	X	X	X	X	X	X	X	E	E	E	I	E
Dowtherm SR-1	100	X	X	X	X	X	X	E	E	E	E	E	E
DP 47,200Flow-Dowi	70	I	I	I	I	I	I	I	I	I	E	E	I
Dry Cleaning Fluid	70	X	X	X	X	X	X	C	I	E	I	I	I
Duro FR-HD	70	I	I	I	I	I	I	I	I	I	E	E	I
Duro Oils	70	I	I	I	I	I	I	I	I	I	E	E	I
Enamels	70	X	X	X	X	X	X	E	E	E	E	C	E
Energol HL-68	70	I	I	I	I	I	I	I	I	I	E	E	E
Energol HLPC-68	70	I	I	I	I	I	I	I	I	I	E	E	E
EP Hydraulic Oils-Chevron	70	I	I	I	I	I	I	I	I	I	E	E	E
Epichlorohydrin	70	X	X	E	E	X	X	X	E	X	I	G	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Epsom Salt (Magnesium Sulfate)	70	E	E	E	E	E	E	E	E	E	E	E	E
Essential Oils	70	I	I	I	I	I	I	I	I	I	E	E	E
Ethane	70	X	X	X	X	E	E	E	I	E	I	I	I
Ethanol (Ethyl Alcohol)	100	E	E	E	E	E	E	E	E	E	E	E	E
Ethanol Amine	100	X	X	E	X	X	X	X	E	X	E	C	E
Ethers	70	X	X	X	X	X	X	X	E	X	E	E	E
Ethyl Acetate	70	X	X	X	G	G	X	X	E	X	E	E	E
Ethyl Acetoacetate	100	X	X	E	X	X	X	X	E	X	E	E	E
Ethyl Acrylate	70	X	X	E	E	X	X	X	E	X	E	G	E
Ethyl Alcohol	70	E	E	E	E	E	E	E	E	E	E	E	E
Ethyl Aldehyde	No hose recommended												
Ethyl Amine	70	C	C	E	E	X	C	X	E	X	E	G	E
Ethyl Benzene	70	X	X	X	X	X	X	X	E	E	E	G	E
Ethyl Benzoate	70	G	G	E	E	X	X	X	G	E	E	I	I
Ethyl Bromide	70	C	I	C	C	X	X	X	G	E	I	G	I
Ethyl Butanol	100	E	I	E	E	I	I	E	E	C	E	E	E
Ethyl Butyl Acetate	100	X	X	X	X	X	X	X	E	I	E	C	E
Ethyl Butyl Alcohol	100	E	I	E	E	I	E	E	E	C	E	E	E
Ethyl Butyl Amine	100	X	X	E	I	I	I	I	I	I	E	I	E
Ethyl Butyraldehyde	100	X	X	X	X	X	X	X	E	I	E	C	E
Ethyl Butyrate	70	X	X	X	X	X	X	X	E	I	E	E	E
Ethyl Caprylate	70	X	X	X	X	X	I	G	I	I	I	I	I
Ethyl Cellosolve	70	X	X	G	C	X	C	X	E	X	E	I	E
Ethyl Cellulose	70	G	G	G	G	G	E	G	E	X	E	E	I
Ethyl Chlorocarbonate	70	X	X	X	G	X	X	X	I	E	I	I	I
Ethyl Chloroformate	70	X	X	X	G	X	X	X	I	X	I	I	I
Ethyl Dichloride	100	X	X	X	X	X	X	X	X	X	E	C	C
Ethyl Ether	70	X	X	C	X	X	X	C	E	X	E	G	E
Ethyl Formate	70	X	X	G	G	G	G	X	E	E	E	I	E
Ethyl Hexanol	70	E	E	E	E	G	G	G	E	G	E	I	E
Ethyl Hexoic Acid	100	X	X	X	X	X	X	X	E	X	E	E	E
Ethyl Hexyl Acetate	100	X	X	X	X	X	X	X	E	I	E	C	E
Ethyl Hexyl Alcohol	100	E	I	E	E	I	E	E	E	C	E	E	E
Ethyl Iodide	70	X	X	C	C	X	X	X	E	E	I	I	G
Ethyl Isobutyl Ether	70	X	X	C	X	X	C	X	E	I	E	I	E
Ethyl Isobutyrate	70	X	X	X	X	X	I	X	I	I	C	I	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Ethyl Mercaptan	70	X	X	X	C	C	G	X	I	G	E	E	I
Ethyl Methyl Ketone	100	X	X	X	X	X	X	X	E	I	E	E	E
Ethyl Oxalate	70	E	E	E	E	X	X	X	E	E	E	E	E
Ethyl Pentachloro-Benzene	70	X	X	X	X	X	X	X	X	E	E	E	I
Ethyl Phthalate	100	X	X	X	X	X	X	X	E	X	E	I	E
Ethyl Propionate	70	X	X	X	X	X	I	X	I	I	I	I	I
Ethyl Propyl Ether	70	X	X	C	X	X	C	X	E	I	E	I	E
Ethyl Propyl Ketone	100	X	X	X	X	X	X	X	E	X	E	E	E
Ethyl Silicate	70	G	G	E	E	E	G	E	E	E	E	E	E
Ethyl Sulfate	100	X	X	X	X	X	X	X	E	X	E	E	E
Ethylchloride	70	C	C	E	G	C	C	E	G	E	E	E	G
Ethylene	70	C	C	G	G	C	I	E	I	E	I	I	I
Ethylene Bromide	70	X	X	G	G	X	X	X	G	G	E	I	G
Ethylene Chloride	70	X	X	G	G	X	X	X	G	G	E	G	G
Ethylene Chloride	70	X	I	C	X	X	I	X	I	I	C	I	I
Ethylene Chlorohydrin	70	C	G	E	E	G	G	X	E	E	E	E	E
Ethylene Dibromide	70	X	X	X	X	X	X	X	X	X	E	C	X
Ethylene Dichloride	70	X	X	C	C	X	X	X	G	E	E	I	G
Ethylene Glycol	70	E	E	E	E	E	E	E	E	E	E	E	E
Ethylene Oxide	70	X	X	C	C	X	X	X	I	X	C	I	I
Ethylene Trichloride	70	X	X	C	C	X	X	X	E	E	E	I	G
Ethlenediamine	70	E	E	E	E	E	C	E	E	X	E	E	E
Ex-Tri	100	X	X	X	X	X	X	X	E	E	E	C	E
Fatty Acids	70	X	X	X	X	X	X	X	E	E	E	G	E
Feran	70	I	I	I	I	I	I	I	I	I	E	I	E
Ferric Bromide	150	E	I	E	E	I	E	E	E	E	E	E	E
Ferric Chloride	150	E	I	E	E	I	E	E	E	E	E	E	E
Ferric Nitrate	70	E	E	E	E	E	E	E	E	E	E	E	E
Ferric Sulfate	150	E	E	E	E	E	E	E	E	E	E	E	E
Ferrous Acetate	100	X	X	E	E	X	E	X	E	X	E	E	E
Ferrous Chloride	150	E	I	E	E	I	E	E	E	C	E	E	E
Ferrous Hdroxide	100	E	I	E	I	I	I	I	E	X	E	E	E
Ferrous Sulfate	70	E	E	E	E	E	E	E	E	E	E	E	E
Fertilizer (liquid manure)	100	I	I	I	E	I	E	I	E	I	E	E	E
Fire Resistant-Hydral	70	I	I	I	I	I	I	I	I	I	E	E	E
Firtec 290, MF	70	I	I	I	I	I	I	I	I	I	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Fish Oil	70	X	X	X	X	X	X	E	E	E	I	I	E
Fixing Solution (Photo)	70	I	I	I	I	I	I	I	I	I	E	E	I
Fluid (Texaco)	70	I	I	I	I	I	I	I	I	I	E	E	I
Fluoboric Acid	70	E	G	E	E	G	E	E	E	X	E	E	E
Fluorinated Cyclic Ethers	70	X	X	E	E	I	I	I	I	E	I	I	I
Fluorine	70	X	X	X	X	C	C	C	X	G	X	E	X
Fluorobenzene	70	X	X	X	X	X	X	X	E	E	E	I	G
Fluorocarbon Oils	70	X	X	E	E	G	I	I	I	I	I	I	G
Fluorolube	70	C	C	E	E	G	E	E	I	G	I	I	I
Fluorosilicic Acid	70	E	G	E	E	E	E	E	E	E	E	E	I
Formaldehyde	70	G	G	E	E	G	E	C	E	G	E	G	E
Formaldehyde 40%	100	C	I	E	E	I	E	E	E	C	E	E	E
Formalin	100	C	I	E	E	I	E	E	E	E	E	E	E
Formamide	70	E	E	E	E	E	I	E	E	X	E	I	E
Formic Acid	70	G	E	E	E	E	E	G	E	C	E	E	E
FR Fluid D	70	I	I	I	I	I	I	I	I	I	E	E	I
FR Hydraulic Fluid	70	I	I	I	I	I	I	I	I	I	E	E	I
Freon 11	70	X	X	X	X	X	E	G	I	E	I	I	I
Freon 12	70	G	G	G	G	E	E	E	I	G	E	E	E
Freon 13	70	E	E	E	E	E	E	E	I	E	I	I	I
Freon 13B1	70	E	E	E	E	E	E	E	I	E	I	I	I
Freon 21	70	X	X	X	X	X	X	X	E	X	E	I	E
Freon 22	70	C	G	E	E	E	E	X	I	X	E	I	E
Freon 31	70	G	G	E	E	E	G	X	I	X	I	I	I
Freon 32	70	E	E	E	E	E	E	E	I	X	I	I	I
Freon 112	70	X	C	X	X	C	E	E	I	E	I	I	I
Freon 113	70	X	G	X	C	E	E	E	I	G	I	I	I
Freon 114	70	E	E	E	E	E	E	E	I	G	I	I	I
Freon 114B2	70	X	C	X	X	C	E	G	I	G	I	I	I
Freon 115	70	E	E	E	E	E	E	E	I	G	I	I	I
Freon 142B	70	G	G	E	G	E	E	E	I	X	I	I	I
Freon 152A	70	E	E	E	E	E	C	E	I	X	I	I	I
Freon 218	70	E	E	E	E	E	E	E	I	E	I	I	I
Freon C316	70	E	E	E	E	E	E	E	I	I	I	I	I
Freon C318	70	E	E	E	E	E	E	E	I	G	I	I	I
Freon 502	70	E	E	E	E	E	I	G	I	G	I	I	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Green Sulfate Liquor	70	E	E	E	E	E	E	E	E	E	E	E	E
Green Vitriol (Ferrous Sulfate)	70	E	E	E	E	E	E	E	E	E	E	I	E
Gulf FR Fluid G-200	70	I	I	I	I	I	I	I	I	I	E	E	I
Gulf FR Fluid P37,P40,P43,P47	70	I	I	I	I	I	I	I	I	I	I	G	I
Halowas Oil	70	X	X	X	X	X	X	X	E	E	E	X	E
Heptanal	70	X	X	C	I	I	X	X	E	X	E	I	E
Heptane	70	X	X	X	X	E	G	E	E	E	E	G	E
Hexaline Glycol	70	I	I	I	I	I	I	I	I	I	E	I	E
Hexane	70	X	X	X	X	E	G	E	E	E	E	E	G
Hexanol (Hexyl Alcohol)	100	E	E	E	G	E	E	E	E	E	E	E	E
Hexene	70	X	X	X	X	G	C	G	E	E	E	X	E
Hexyl Alcohol	70	E	E	E	G	E	E	E	E	E	E	E	E
Hexyl Methyl Ketone	100	X	X	X	X	X	X	X	E	X	E	E	E
Hi-Tri	100	X	X	X	X	X	X	X	E	E	E	C	E
H-I solution	70	X	X	X	X	X	X	X	I	I	I	I	E
Houghto-Safe 1055,1110,1115,1120,	70	I	I	I	I	I	I	I	I	I	E	E	E
Houghto-Safe,271416,520,&620,625,	70	I	I	I	I	I	I	I	I	I	E	E	E
Houghto-Safe (5046)	70	I	I	I	I	I	I	I	I	I	E	E	E
Hy-Chock Oil	70	I	I	I	I	I	I	I	I	I	E	E	E
Hydrofluoric Acid	70	I	I	I	I	I	I	I	I	I	E	I	E
Hydrafluid 760 (Texaco & Houghton)	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydrafluid , AZR & O, ABAAC	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydrasol A	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydraulic Fluid (Phosphate Ester Base)	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydraulic Fluid (Water Glycol Base)	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydraulic Fluid HF-18, HF-20	70	I	I	I	I	I	I	I	I	I	E	E	I
Hydraulic Fluid HF-31	70	I	I	I	I	I	I	I	I	I	E	E	E
Hydraulic Oil (Petroleum Base)	70	X	X	X	X	I	G	E	E	E	E	E	E
Hydrazine	70	G	E	E	E	I	G	G	I	X	E	E	E
Hydrochloric Acid - 15%	70	E	X	G	C	X	E	X	E	I	E	G	E
Hydrochloric Acid - 10%	125	X	X	X	E	X	X	X	E	I	E	E	E
Hydrochloric Acid - 25%	70	E	G	E	E	I	E	C	E	E	E	I	E
Hydrochloric Acid -37% (cold)	70	E	I	E	G	I	E	X	E	I	E	E	E
Hydrobromic Acid (37%)	150	E	I	E	E	I	E	X	E	I	E	E	G
Hydrocyanic Acid	70	G	G	E	E	I	E	G	I	E	E	E	E
Hydrocyanic Acid -20%	70	I	I	I	I	I	I	I	I	I	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Hydrocyanic Acid -98%	70	I	I	I	I	I	I	I	I	I	E	E	E
Hydrofluoric Acid	70	X	X	X	X	X	X	X	E	X	E	E	E
Hydrofluoric Acid	125	X	X	X	X	X	X	X	X	X	E	X	X
Hydrofluoric Acid - 10%	100	X	X	X	X	X	X	X	I	I	E	I	C
Hydrofluoric Acid - 50%	70	G	X	G	G	G	E	X	E	E	E	E	E
Hydrofluoric Acid -75%	70	X	X	C	C	X	E	X	E	E	E	E	E
Hydrofluoric Acid-Anhydrous	70	X	X	X	X	X	E	X	I	X	E	I	I
Hydrofluosilicic Acid (Fluosilicic Acid)	150	E	I	E	E	I	E	E	I	I	E	E	C
Hydroflurosilicic Acid (Fluorisilic Acid)	70	I	I	I	I	I	I	I	I	I	E	I	E
Hydrogen Chloride	70	I	I	I	I	I	I	I	I	I	E	E	E
Hydrogen Dioxide over 10%	70	I	I	I	I	I	I	I	I	I	I	I	G
Hydrogen Fluoride	70	I	I	I	I	I	I	I	I	I	I	G	I
Hydrogen Gas	70	X	X	E	X	E	E	E	E	E	E	E	E
Hydrogen Peroxide (Conc.)	70	X	X	C	G	X	E	X	E	E	E	I	G
Hydrogen Peroxide - 3%	70	E	E	E	E	E	E	E	E	E	E	I	E
Hydrogen Peroxide -10%	70	I	I	I	I	I	I	I	I	I	E	G	G
Hydrogen Peroxide - 30%	70	C	C	C	E	C	E	C	E	E	E	G	G
Hydrogen Peroxide - 50%	100	X	X	X	X	X	X	X	X	X	E	X	X
Hydrogen Peroxide - 70%	70	X	X	X	X	X	X	X	X	X	E	X	X
Hydrogen Peroxide - 90%	70	X	X	X	X	X	X	X	X	X	E	X	X
Hydrogen Sulfide (Wet)	70	X	X	X	X	X	X	X	E	X	E	I	E
Hydrogen Sulfide (Wet)	100	X	X	X	X	X	X	X	E	X	E	I	E
Hydrolube (Water Glycol)	70	I	I	I	I	I	I	I	I	I	I	I	I
Hydrolubic Oil (Houghton)	70	I	I	I	I	I	I	I	I	I	E	E	E
Hydroquinone	70	G	X	C	G	X	C	X	I	G	E	E	I
Hypo (Sodium Thiosulfate)	70	E	E	E	E	E	E	E	E	E	E	I	E
Hypochlorous Acid	70	E	X	E	E	X	X	X	I	E	E	E	I
I-Chloro-I-Nitroethane	70	X	X	X	X	X	X	X	I	X	E	I	I
Industron 53	70	I	I	I	I	I	I	I	I	I	E	E	E
Ink (printer's)	70	I	I	I	I	I	I	I	I	I	E	E	E
Ink Oil	70	I	I	I	I	I	I	I	I	I	E	G	E
Insulating Oil (Transformer)	70	I	I	I	I	I	I	I	I	I	E	E	E
Iodine	70	X	X	C	G	C	E	G	E	G	E	E	E
Iodine Pentafluoride	70	X	X	X	X	X	X	X	I	X	C	I	I
Iodine, in Alcohol	70	I	I	I	I	I	I	I	I	I	E	E	E
Iodoform (Triiodomethane)	70	X	X	X	C	X	C	X	I	I	C	I	I

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Iris Fluid 902	70	I	I	I	I	I	I	I	I	I	E	E	E
Iris Fluid 905	70	I	I	I	I	I	I	I	I	I	E	E	E
Iron Acetate	100	X	X	E	X	X	X	X	E	X	E	E	E
Iron Hydroxide	100	X	X	X	X	X	X	X	E	X	E	E	E
Iron Salts	150	E	I	E	E	I	E	E	E	E	E	E	E
Iron Sulfate	150	E	I	E	E	I	E	E	E	E	E	E	E
Iron Sulfite	70	I	I	I	I	I	I	I	I	I	E	I	E
Isoamyl Acetate	100	X	X	X	X	X	X	X	E	X	E	C	E
Isoamyl Alcohol	70	E	E	E	E	E	E	C	I	E	E	I	E
Isoamyl Bromide	100	X	X	X	X	X	X	X	C	I	E	I	C
Isoamyl Butyrate	100	X	X	X	X	X	X	X	I	I	E	C	G
Isoamyl Chloride	100	I	I	I	I	I	I	I	I	I	E	I	G
Isoamyl Ether	100	I	I	I	I	I	I	I	E	I	E	I	E
Isoamyl Phthalate	70	X	X	X	X	X	X	X	E	I	E	I	E
Isobutane	No hose recommended												
Isobutanol	100	E	I	E	E	I	E	E	E	C	E	E	E
Isobutyl Acetate	70	X	X	E	X	X	X	X	E	X	E	I	E
Isobutyl Alcohol	70	E	G	E	E	E	E	C	E	E	E	E	E
Isobutyl Ether	100	X	X	X	X	X	X	X	X	I	E	I	E
Isobutylene	100	X	X	X	X	X	X	X	E	E	E	C	E
Isobutyric Acid	70	E	I	E	E	G	I	X	I	I	I	I	I
Isocyanate Toluene Diisocyanate	70	I	I	I	I	I	I	I	I	I	E	E	E
Isododecane	70	X	X	X	X	E	E	E	I	E	E	I	I
Isooctane	70	X	X	X	X	E	E	E	E	E	E	G	G
Isoocytl Thioglycolate	70	I	I	I	I	I	I	I	I	I	E	E	E
Isopentane	70	X	X	X	I	I	X	E	E	E	E	I	G
Isophorone	70	X	X	G	C	X	X	X	I	X	I	I	G
Isopropanol (Isopropyl Alcohol)	70	E	G	E	E	E	E	G	E	E	E	E	E
Isopropanol Amine	70	I	I	I	I	I	I	I	I	I	E	I	E
Isopropyl Acetate	70	X	X	G	G	X	X	X	E	X	E	E	E
Isopropyl Alcohol	70	E	G	E	E	E	E	G	E	E	E	E	E
Ispropyl Benzene	70	X	X	X	X	X	X	X	E	E	E	I	E
Isopropyl Chloride	70	X	X	X	X	X	X	X	G	E	E	I	G
Ispropyl Ether	70	X	X	X	X	C	C	G	E	X	E	E	E
Ispropyl Toluene	100	X	X	X	X	X	X	X	E	E	E	G	E
Jet Fuel JP-3	70	X	X	X	X	G	C	E	E	E	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Jet Fuel JP-4	70	X	X	X	X	G	C	E	E	E	E	E	E
Jet Fuel JP-5	70	X	X	X	X	G	C	E	E	E	E	E	E
Jet Fuel JP-6	70	I	I	I	I	I	I	I	I	I	E	E	I
Jet Fuel JP-X	70	I	I	I	I	I	I	I	I	I	E	E	I
JMLO	70	I	I	I	I	I	I	I	I	I	E	I	X
Kerosene	70	X	X	X	X	G	X	E	E	E	E	E	E
Ketchup	100	X	X	X	E	X	X	E	E	I	E	E	E
Ketone	70	X	X	X	X	X	X	X	E	E	E	G	E
Ketones	70	X	X	X	X	X	X	X	E	X	E	E	E
Laquer Solvents	70	X	X	X	X	X	X	X	E	X	E	E	E
Laquers	70	X	X	X	X	X	X	X	E	X	E	E	E
Lactic Acid (cold)	70	E	E	E	E	E	E	C	E	E	E	E	E
Lactic Acid (hot)	70	X	X	X	X	X	C	X	I	E	I	I	I
Lactol (Aliphalic Naphtha)	70	X	I	X	I	E	E	E	E	E	E	E	E
Lard	70	X	X	G	E	G	G	E	E	E	E	E	E
Lard Oil	70	X	X	X	X	G	X	E	E	E	E	E	E
Lasso Ag Spray	70	I	I	I	I	I	I	I	I	I	E	E	E
Latex	70	I	I	I	I	I	I	I	I	I	I	G	I
Lauryl Alcohol	70	E	E	E	E	E	E	E	E	G	E	E	E
Lavender Oil	70	X	X	X	X	X	X	G	G	E	E	I	G
Lead Acetate	70	E	C	E	E	E	C	G	E	X	E	E	E
Lead Arsenate	70	I	I	I	I	I	I	I	I	I	E	E	E
Lead Chloride	70	G	I	I	I	G	E	I	I	I	I	I	I
Lead Nitrate	70	E	E	E	E	E	E	E	E	I	E	E	E
Lead Salt	70	I	I	I	I	I	I	I	I	I	I	I	E
Lead Sulfamate	70	E	E	E	E	E	E	G	E	E	E	E	E
Lead Sulfate	150	E	I	E	E	I	E	E	E	E	E	E	E
Lead Tetraethyl	100	I	I	I	I	I	I	I	I	I	E	I	I
Lead Tetraethyl	70	I	I	I	I	I	I	I	I	I	E	X	I
Lecithin	70	I	I	I	I	I	I	I	I	I	E	E	I
Ligroin (Petroleum Ether)	70	X	X	X	X	G	X	E	E	E	E	G	E
Lime (Calcium Oxide)	70	E	E	E	E	E	E	E	E	I	E	E	E
Lime Bleach	70	E	E	E	E	E	E	I	I	E	E	E	I
Lime Sulfur	70	X	X	E	E	E	E	X	E	E	E	E	E
Lindane	70	I	I	I	I	I	I	I	I	I	E	E	E
Linoleic Acid	70	X	X	X	X	X	X	G	I	G	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Fluorocarbon (Viton/Fluorel)	Fluorocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Mercury Cyanide	70	E	E	E	E	G	E	E	E	I	E	E	E
Mercury Salts	70	I	I	I	I	I	I	I	I	I	E	I	E
Mercury Vapor	70	I	I	I	I	I	I	I	I	I	E	E	I
Mesityl Oxide	70	X	X	G	G	X	X	X	E	X	E	E	E
Metallic Soaps	70	I	I	I	I	I	I	I	I	I	I	I	I
Methallyl Alcohol	100	E	E	E	E	E	E	E	E	C	E	C	E
Methallyl Chloride	70	I	I	I	I	I	I	I	I	I	E	I	E
Methane	70	C	C	X	X	G	G	E	G	G	E	E	G
Methanol (Formaldehyde)	70	G	G	E	E	G	E	C	E	G	E	E	E
Methanol (Methyl Alcohol)	70	E	E	E	E	E	E	E	E	G	E	E	E
Methoxychlor (Insecticide)	70	I	I	I	I	I	I	I	I	I	E	E	I
Methacrylic Acid	70	X	X	X	X	X	G	G	E	G	E	I	E
Methyl Acetate	100	X	X	E	E	G	X	X	E	X	E	G	E
Methyl Acetocetate	100	X	X	X	X	X	X	X	E	X	E	E	E
Methyl Acetone	No hose recommended												
Methyl Alcohol	100	E	I	E	E	I	E	E	E	X	E	E	E
Methyl Amine	70	E	E	E	E	E	I	G	I	I	I	G	I
Methyl Amine - 60%	70	I	I	I	I	I	I	I	I	I	E	E	E
Methyl Amine - 99%	70	I	I	I	I	I	I	I	I	I	E	E	E
Methyl Amyl Alcohol	100	E	E	E	E	E	E	E	E	C	E	I	E
Methyl Amyl Carbinol	100	E	X	E	E	X	E	E	E	X	E	E	E
Methyl Amyl Ketone	100	X	X	X	X	X	X	X	E	X	E	C	E
Methyl Aniline	70	E	E	E	E	X	I	X	I	I	E	I	I
Methyl Benzene	100	E	I	E	X	I	E	E	E	C	E	E	E
Methyl Bromide	70	X	X	G	G	X	X	G	I	E	E	E	I
Methyl Butanol	100	E	I	E	E	I	E	E	E	C	E	E	E
Methyl Butanone	100	X	X	X	X	X	X	X	E	X	E	C	E
Methyl Buty Ketone (MBK)	70	X	X	E	E	X	X	X	E	X	E	E	E
Methyl Butyrate	70	X	X	X	X	E	X	I	I	I	I	I	I
Methyl Carbitol	100	X	X	X	X	I	X	X	E	X	E	E	E
Methyl Cellosolve	70	X	X	E	E	C	G	C	E	X	E	E	E
Methyl Chloride	70	X	X	C	C	X	X	X	E	E	E	G	E
Methyl Cyclohexane	100	X	X	X	X	X	X	X	E	X	E	I	E
Methyl Cyclopentane	70	X	X	X	X	X	X	X	I	G	E	I	I
Methyl Ether	70	X	X	C	X	C	G	E	E	C	E	I	E
Methyl Ethyl Ketone (MEK)	70	X	X	G	E	C	X	X	E	X	E	G	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Methyl Formate	70	X	X	E	E	E	C	X	E	I	E	E	E
Methyl Hexanol	100	C	I	E	E	I	E	E	E	E	E	E	E
Methyl Hexyl Ketone	100	X	X	X	X	X	X	X	E	X	E	C	E
Methyl Iodide	70	E	I	E	E	X	I	X	I	I	I	I	I
Methyl Isobutyl Carbinol	70	E	E	E	E	E	E	E	E	E	E	I	E
Methyl Isobutyl Ketone (MIBK)	70	X	X	G	G	X	X	X	E	X	E	G	E
Methyl Isopropyl Ketone	70	X	X	G	G	X	X	X	E	X	E	G	E
Methyl Methacrylate	70	X	X	X	C	X	E	X	E	X	E	G	E
Methyl Normal Amyl Ketone	100	X	X	X	X	X	X	X	E	X	E	C	E
Methyl Oleate	70	X	X	E	E	X	X	X	E	E	E	I	E
Methyl Salicylate	70	C	C	C	C	X	X	X	I	I	E	E	I
Methylacrylate	70	X	X	E	E	E	X	X	I	X	I	G	I
Methylacrylic Acid	70	X	X	E	E	E	X	X	I	X	I	I	I
Methylallyl Acetate	100	X	X	X	X	X	X	X	E	X	E	E	E
Methylallyl Chloride	100	X	X	X	X	X	X	X	E	X	E	I	E
Methylamyl Acetate	70	X	X	C	X	X	G	X	E	X	E	I	E
Methylene Bromide	100	X	X	X	X	X	X	X	C	C	E	E	G
Methylene Chloride	No hose recommended												
Methylene Dichloride	70	X	I	I	I	I	I	I	I	I	I	I	I
Milk	70	G	G	E	E	E	E	I	E	E	E	E	E
Mineral Oil	70	X	X	X	X	G	G	E	E	E	E	E	E
Mineral Spirits (Naphata)	70	X	X	X	X	G	G	E	E	E	E	E	E
Mobil Therm 603	70	I	I	I	I	I	I	I	I	I	E	E	I
Mobilmer S122	70	I	I	I	I	I	I	I	I	I	E	E	I
Molasses	100	E	E	E	E	E	E	E	E	E	E	E	E
Monobromobenzene	100	X	X	X	X	X	X	X	C	E	E	C	G
Monochloroacetic Acid	100	X	X	X	X	X	X	X	E	I	E	E	E
Monochlorobenzene	70	X	X	X	X	X	X	X	G	E	E	G	G
Monoethanolamine	70	E	E	E	E	X	X	C	E	X	E	G	E
Monoethyl Amine	100	I	I	E	I	I	I	I	E	I	E	C	E
Monoisopropanol Amine	100	X	X	X	X	X	X	X	E	I	E	C	E
Monomethyl Aniline	70	X	X	C	G	X	X	X	X	G	E	I	X
Monomethylether	70	X	X	C	X	C	G	E	E	C	E	I	E
Monovinyl Acetylene	70	E	E	E	E	E	E	E	I	E	I	I	I
Motor Oil	70	X	X	X	X	G	G	E	E	E	E	C	E
Motor Oils	135	X	X	X	X	X	X	E	E	E	E	G	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Mould Oil	70	X	X	X	X	X	X	E	E	E	E	G	E
Muriatic Acid	125	E	I	X	X	X	X	X	E	I	E	E	E
Muriatic Acid (Hydrochloric Acid)	70	E	G	E	G	C	E	X	E	E	E	G	E
Muriatic Gas (Dichlorodiethyl sulfide)	70	E	G	E	E	E	E	I	I	I	E	E	I
Naphthalene	70	X	X	X	X	X	X	X	E	E	E	I	E
Naphthalenic Acid	70	X	X	X	X	X	X	E	E	E	E	I	E
Naphthenic Acid	70	X	X	X	X	X	X	E	E	E	E	I	E
Naptha, Petroleum	70	X	X	X	X	G	G	E	E	E	E	E	E
Natural Gas(85% Methane)	70	G	G	X	X	E	E	E	E	E	E	I	E
Neatsfoot Oil	70	X	X	E	X	X	E	E	I	E	I	I	I
Neohexane	100	X	X	X	X	X	X	E	E	E	E	C	E
Neutral Oil	100	X	X	X	X	X	X	X	E	X	E	C	E
Neu-Tri	100	X	X	X	X	X	X	X	E	E	E	C	E
Neville Acid	70	X	X	E	E	X	X	X	I	E	I	I	I
n-Hexaldehyde	70	X	X	E	E	E	C	X	E	X	E	E	E
Nickel Acetate	70	E	X	E	E	E	X	E	E	X	E	E	E
Nickel Chloride	150	E	I	E	E	I	E	E	E	E	E	E	E
Nickel Nitrate	150	E	I	E	E	I	E	E	E	E	E	E	E
Nickel Plating Solution	70	I	I	I	I	I	I	I	I	I	I	E	E
Nickel Salts	70	I	I	I	I	I	I	I	I	I	I	E	E
Nickel Sulfate	150	E	I	E	E	I	E	E	E	E	E	E	E
Nicotine Sulfate	70	I	I	I	I	I	I	I	I	I	I	I	E
Niter (Potassium Nitrate)	70	E	E	E	E	E	E	E	E	E	E	I	E
Niter Cake (Sodium Bisulfate)	70	E	E	E	E	E	E	E	E	E	E	E	E
Nitrana 2	70	I	I	I	I	I	I	I	I	I	I	I	E
Nitrana 3	70	I	I	I	I	I	I	I	I	I	E	I	E
Nitration Benzol	70	I	I	I	I	I	I	I	I	I	E	I	E
Nitric Acid	70	X	X	X	X	X	G	X	E	C	E	I	I
Nitric Acid (conc)	70	X	X	X	X	X	G	X	E	C	E	I	I
Nitric Acid (Dilute)	70	X	X	E	E	G	E	X	E	E	E	I	I
Nitric Acid - 10%	70	X	X	X	X	X	X	X	C	C	E	C	G
Nitric Acid 25%	100	X	X	X	X	X	X	X	X	X	E	G	G
Nitric Acid 40% - 60%	70	X	X	X	X	X	X	X	X	X	E	G	X
Nitric Acid - Red-Fuming	70	X	X	X	X	X	X	X	X	X	E	X	X
Nitro Benzene	70	X	X	X	X	X	X	X	E	G	E	G	E
Nitroethane	70	E	E	E	E	X	E	X	E	X	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Nitrogen Gas	70	E	E	E	E	E	E	E	E	E	E	E	E
Nitrogen Oxide UP TO 50%	100	E	I	E	E	I	E	E	E	E	E	E	E
Nitrogen Tetoxide	70	X	X	G	C	X	X	X	I	X	E	I	I
Nitroglycerine	70	I	I	I	I	I	I	I	I	I	E	I	E
Nitromethane	70	E	G	E	E	G	G	X	E	X	E	E	E
Nitrooctane	70	I	I	I	I	I	I	I	I	I	E	I	E
Nitropropane	70	C	C	E	E	X	X	X	E	X	E	E	E
Nitrosyl Chloride	70	I	I	I	I	I	I	I	I	I	E	E	E
Nitrous Acid	70	I	I	I	I	I	I	I	I	I	E	I	E
Nitrous Acid up to 10%	70	I	I	I	I	I	I	I	I	I	E	E	E
n-Octane	70	I	I	I	I	I	I	I	I	I	I	G	I
Nonenes	70	I	I	I	I	I	I	I	I	I	E	I	E
Nyvac 20 (WG), 30 (WG)	70	I	I	I	I	I	I	I	I	I	E	E	E
Nyvac FR Fluid	70	I	I	I	I	I	I	I	I	I	E	E	E
Nyvac FR200 Fluid	70	I	I	I	I	I	I	I	I	I	E	E	E
O-Chloronaphthalene	70	I	I	I	I	I	I	I	I	I	I	X	I
Octachlorotoluene	70	X	X	X	X	X	X	X	I	E	I	I	I
Octadecane	70	X	X	X	X	E	E	E	I	E	I	I	I
Octane	70	X	X	X	G	G	G	I	E	E	E	I	G
Octulene Glycol	70	I	I	I	I	I	I	I	I	I	E	I	E
Octyl Acetate	100	X	I	X	X	X	E	X	E	X	E	C	E
Octyl Alcohol	70	E	E	C	X	E	E	E	E	E	E	E	E
Octyl Aldehyde	100	X	X	X	X	X	X	X	E	X	E	I	E
Octyl Amine	100	X	X	X	X	X	X	X	C	X	E	C	E
Octyl Carbinol	100	E	I	E	E	E	E	E	E	X	E	E	E
Octynol	70	I	I	I	I	I	I	I	I	I	E	I	E
o-Dichlorobenzene	70	X	X	X	X	X	X	X	G	E	E	G	G
Oil	100	X	X	X	X	C	I	E	E	E	E	C	E
Oil of Turpentine	100	X	X	X	X	G	X	G	E	E	E	G	E
Oils, Animal	100	X	X	X	X	G	I	E	E	E	E	G	E
Oleic Acid	70	X	X	C	C	G	G	E	E	I	E	E	E
Oleum (Fuming Sulfuric Acid)	70	X	X	X	X	X	X	X	X	E	E	X	X
Oleum Spirits (Petroleum Distillate)	70	X	X	X	X	G	X	E	E	E	E	E	E
Olive Oil	70	X	X	G	G	G	G	E	E	E	E	E	E
Organic Fatty Acids	100	X	X	X	X	X	X	E	E	E	E	C	E
Othodichlorobenzene	100	X	X	X	X	X	X	X	E	E	E	C	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Oxalic Acid	100	X	X	X	E	X	G	X	E	E	E	G	E
Oxygen 200-400F	No hose recommended												
Oxygen - Cold	70	X	X	X	X	E	E	X	E	E	E	I	E
Ozone	70	X	X	E	E	C	E	X	E	E	E	G	E
Pacemaker 150T,200T,500T(Citgo)	70	I	I	I	I	I	I	I	I	I	E	E	I
Paint (water base)	70	E	E	E	E	E	E	E	E	E	E	E	E
Paint Solvents (oil base)	70	X	X	X	X	C	E	E	E	E	E	E	E
Paint Thinner, Duco	70	X	X	X	X	X	X	X	I	G	E	I	I
Paints (oil base)	70	X	X	X	X	X	X	X	E	E	E	E	E
Palm Oil	70	X	X	X	X	X	X	E	E	I	E	I	E
Palmitic Acid	70	G	G	G	G	G	X	E	E	E	E	E	E
Papermaker's Alum	150	E	I	E	E	I	E	E	E	E	E	E	E
Para San 10%	70	I	I	I	I	I	I	I	I	I	E	I	E
Paradichlorobenzene	70	X	X	X	X	X	X	X	I	E	E	I	I
Paradichlorobenzol	100	X	X	X	X	X	X	X	E	E	E	I	G
Paraffin Wax	150	X	X	X	X	E	G	E	E	E	E	E	E
Paraformaldehyde	70	I	I	I	I	I	I	I	I	I	E	G	E
Paraldehyde	100	X	X	X	X	X	X	C	E	X	E	I	E
Paraxylene	100	X	X	X	X	X	X	X	E	E	E	C	E
Paris Green & Lime 37%	70	I	I	I	I	I	I	I	I	I	E	I	E
p-Cymene	70	X	X	X	X	X	X	X	E	E	E	G	G
Peanut Oil	70	X	X	C	C	G	G	E	I	E	E	E	I
Pelargonic Acid	70	X	X	E	I	I	X	E	E	I	E	I	E
Pentachloroethane	100	X	X	X	X	X	X	X	E	E	E	G	E
Pentachlorophenol	70	X	X	E	I	X	I	X	I	E	E	E	I
Pentane	70	X	X	X	X	E	E	E	E	E	E	X	G
Pentanol	100	E	I	E	E	I	E	E	E	C	E	E	E
Pentasol	70	I	I	I	I	I	I	I	I	I	I	G	I
Perchloric Acid	70	X	X	E	E	E	G	X	E	E	E	G	E
Perchloroethylene	100	X	X	X	X	X	X	X	E	E	E	G	G
Petrolatum	70	I	I	I	I	I	I	I	I	I	E	I	E
Petroleum Crude	100	X	X	X	X	G	G	E	E	E	E	I	E
Petroleum Ether	100	X	X	X	X	X	X	E	E	E	E	I	E
Petroleum Oils	70	X	X	X	X	G	X	E	E	E	E	I	E
Petroleum -Above 250F		X	X	X	X	X	X	X	I	E	E	I	X
Petroleum -Below 250F		X	X	X	X	X	X	E	I	E	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Phenetole (Phenyl Ethyl Ether)	70	X	X	X	X	X	X	X	I	X	E	I	I
Phenol	125	X	X	X	X	X	X	X	E	E	E	G	E
Phenolates	70	I	I	I	I	I	I	I	I	I	I	X	I
Phenyl Chloride	100	X	X	X	X	X	X	X	E	E	E	C	E
Phenyl Ethyl Ether	70	X	X	X	X	X	X	X	I	X	E	I	I
Phenyl Sufonic Acid	100	X	X	X	X	X	X	X	C	C	E	C	X
Phenylbenzene	70	X	X	X	X	X	X	X	I	E	E	I	I
Phenylhydrazine	70	E	E	G	G	X	X	X	E	E	E	I	E
Phorone (Disopropylidene Acetone)	70	X	X	G	C	X	X	X	I	X	E	E	I
Phosphate Esters	150	X	X	E	E	X	X	X	E	X	E	C	E
Phosphoric Acid -10%	150	E	I	E	E	I	E	E	E	X	E	I	E
Phosphoric Acid -50%	70	G	G	E	E	E	E	G	E	E	E	E	E
Phosphoric Acid -85%	70	C	X	E	E	G	E	X	E	E	E	G	E
Phosphoric Acid (conc.)	70	X	X	C	E	X	C	X	E	E	E	I	E
Phosphorous Oxychloride	70	X	I	X	I	X	X	I	I	I	I	I	I
Phosphorous Trichloride	70	X	X	E	E	X	X	X	I	E	E	I	I
Photographic Developers	70	I	I	I	I	I	I	I	I	I	E	G	G
Photographic Emulsions	70	I	I	I	I	I	I	I	I	I	E	E	E
Photographic Fixing	70	I	I	I	I	I	I	I	I	I	E	E	E
Phthalic Acid	70	I	I	I	I	I	I	I	I	I	E	E	E
Pickling Solution	70	X	X	C	C	X	G	X	E	C	E	I	E
Picric Acid (water solution)	70	E	G	E	E	E	E	E	I	E	E	G	I
Picric Acid - Molten	70	C	C	C	E	C	E	X	I	E	E	I	I
Pine Coating Oil	70	I	I	I	I	I	I	I	I	I	I	I	E
Pine Oil	100	X	X	X	X	X	X	C	E	E	E	E	E
Pine Tar	70	I	I	I	I	I	I	I	I	I	I	I	E
Pinene	150	X	X	X	X	X	X	E	E	E	E	E	E
Piperazine Hydrochloride	70	I	I	I	I	I	I	I	I	I	E	E	E
Piperidine	70	X	X	X	X	X	X	X	I	X	E	I	E
Pitch	70	I	I	I	I	I	I	I	I	I	E	E	E
Plating Solution -Chrome	70	X	X	E	E	X	X	I	I	E	E	E	E
Plating Solution -Others	70	X	X	E	E	X	E	E	E	E	E	I	E
Polyester Resin	70	I	I	I	I	I	I	I	I	I	E	E	E
Polyethylene Glycol	150	E	E	E	E	E	E	E	E	E	E	E	E
Polyurethane Foam	70	I	I	I	I	I	I	I	I	I	E	E	E
Polyvinyl Acetate	70	G	X	E	E	G	E	I	E	E	E	I	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Potassium Acetate	100	X	X	E	C	X	X	X	E	X	E	E	E
Potassium Bicarbonate	70	E	E	E	E	E	E	E	E	E	E	E	E
Potassium Bisulfate	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Bisulfite	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Borate	70	E	E	E	E	E	E	E	I	I	I	I	I
Potassium Bromate	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Bromide	70	E	E	E	E	E	E	E	I	I	E	E	E
Potassium Carbonate	70	I	I	I	I	I	I	I	I	I	E	I	E
Potassium Chloride	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Chromate	150	X	X	X	X	X	X	X	G	G	E	G	G
Potassium Cupro Cyanide	70	E	E	E	E	E	E	E	I	E	E	E	E
Potassium Cyanide	70	E	E	E	E	E	E	E	E	E	E	E	E
Potassium Dichromate	150	X	X	X	X	X	X	X	E	E	E	G	G
Potassium Fluoride	70	I	I	I	I	I	I	I	I	I	E	E	E
Potassium Hydrate	150	I	I	E	E	I	I	I	E	X	E	E	E
Potassium Hydroxide	150	C	C	E	I	C	C	X	E	X	E	E	G
Potassium Hypochlorite	70	G	C	C	I	C	E	X	I	I	E	I	I
Potassium Iodide	70	I	I	I	E	E	E	E	I	I	E	E	E
Potassium Nitrate	150	E	I	E	E	I	E	E	E	E	E	E	E
Potassium Nitrite	70	I	I	I	E	E	E	I	I	I	I	I	I
Potassium Permanganate	70	E	E	E	E	G	E	E	I	I	E	E	E
Potassium Phosphate	70	I	I	I	E	E	E	I	I	I	E	E	E
Potassium Salts	70	I	I	I	I	I	I	I	I	I	E	I	E
Potassium Silicate	150	E	I	E	E	I	E	E	E	E	E	E	E
Potassium Sulfate	150	E	I	E	E	I	E	E	E	E	E	E	E
Potassium Sulfide	150	E	I	E	E	I	E	E	E	E	E	I	E
Potassium Sulfite	150	E	I	E	E	I	E	E	E	E	E	E	E
Potassium Thiosulfate	70	E	I	I	I	E	E	E	I	I	E	I	E
Potassium Carbonate	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Chloride	150	E	I	E	I	E	E	E	E	E	E	E	E
Potassium Ferro Cyanide	70	I	I	I	I	I	I	I	I	I	E	E	I
Prestone Antifreeze (Ethylene Glycol)	150	E	E	E	E	E	E	E	E	E	E	I	E
Primatol A,SP (Ag.Spray)	70	I	I	I	I	I	I	I	I	I	I	I	I
Producer Gas	70	X	X	G	X	E	E	E	I	E	E	I	I
Propane	Use only recommended Propane hose												
Propanol	100	E	I	E	E	I	E	E	E	X	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Fluorocarbon (Viton/Fluorel)	Fluorocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Rapeseed Oil	70	X	X	E	E	E	G	E	I	E	E	E	I
Red Oil (Oleic Acid)	70	X	X	X	C	G	G	E	E	F	E	E	E
Refined Oil	70	X	X	X	X	C	C	E	E	E	E	I	E
Refined Wax	100	X	X	X	X	X	X	E	E	E	E	E	E
Regal Oils R & O	70	X	I	I	I	I	I	I	I	I	E	E	E
Richfield "A" 100%	70	I	I	I	I	I	I	I	I	I	E	I	E
Richfield "A" Weed Killer	70	I	I	I	I	I	I	I	I	I	E	E	E
Richfield "D" 33%	70	I	I	I	I	I	I	I	I	I	E	I	E
Rosia Oil	70	I	I	I	I	I	I	I	I	I	E	I	E
Rosin Oil	70	X	X	X	X	E	E	E	E	E	E	I	E
Rotenone & Water	70	I	I	I	I	I	I	I	I	I	E	I	E
Rubilene Oils	70	I	I	I	I	I	I	I	I	I	E	E	I
Safetytex 215	70	I	I	I	I	I	I	I	I	I	E	E	I
Sal Ammoniac (Ammonium Chloride)	150	E	E	I	E	E	E	E	E	E	E	E	E
Sal Volatile (Ammonium Carbonate)	70	E	E	E	G	G	I	X	E	E	E	E	E
Salicylic Acid	70	E	G	E	E	G	E	G	I	E	E	E	I
Salt Water	70	E	E	E	E	G	E	E	E	E	E	E	E
Salt peter (Potassium Nitrate)	150	E	I	E	E	E	E	E	E	E	E	I	E
Santosafe W-G15, W-G20, W-G30	70	I	I	I	I	I	I	I	I	I	E	E	I
Sauerkraut	100	I	E	I		E	I	E	E	I	E	I	E
Secondary Buytlacetate	70	I	I	I	I	I	I	I	I	I	E	I	E
Sevin	70	I	I	I	I	I	I	I	I	I	E	G	G
Sewage	70	G	G	G	G	G	E	E	E	E	E	E	E
SFR Fluid B (Shell)	70	I	I	I	I	I	I	I	I	I	E	E	I
SFR Fluid C (Shell)	70	I	I	I	I	I	I	I	I	I	E	E	I
Shell DD	70	I	I	I	I	I	I	I	I	I	I	I	E
Shellac	70	I	I	I	I	I	I	I	I	I	E	E	E
Silica Gell	70	I	I	I	I	I	I	I	I	I	E	I	E
Silicate Esters	70	X	X	X	X	E	E	G	I	E	I	I	I
Silicate of Soda	70	E	E	E	E	E	E	E	E	E	E	I	E
Silicone Greases	70	E	E	E	E	E	E	E	I	E	E	G	I
Silicone Oils	70	E	E	E	E	E	E	E	I	E	E	G	I
Silver Cyanide	70	E	I	I	I	E	I	I	I	I	E	E	I
Silver Nitrate	70	E	E	E	E	E	E	E	E	E	E	E	E
Silver Salt	70	I	I	I	I	I	I	I	I	I	I	I	E
Skydrol 500	70	X	X	G	E	X	X	X	E	X	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Skydrol 7000	70	X	X	E	E	X	X	X	E	G	E	E	E
Slaked Lime (Calcium Hydroxide)	70	E	E	E	E	E	E	E	E	E	E	I	E
Soap Oil	70	X	X	X	X	C	C	E	E	E	E	E	E
Soap Solutions	70	G	G	E	E	G	E	E	E	E	E	E	E
Soda Ash (Sodium Carbonate)	70	E	E	E	E	E	E	E	E	E	E	E	E
Soda Niter (Sodium Nitrate)	70	E	E	E	E	E	E	G	E	I	E	I	E
Soda Water	70	E	E	E	E	E	E	E	E	E	E	E	E
Soda, Caustic	100	E	C	E	E	I	I	C	E	E	E	E	E
Soda, Lime	100	E	I	E	E	E	C	C	E	X	E	E	E
Soda, Niter	100	E	I	E	E	I	E	E	E	E	E	E	E
Sodan	70	I	I	I	I	I	I	I	I	I	E	I	E
Sodium Aetate	70	E	C	E	E	G	E	G	E	X	E	E	E
Sodium Aluminate	100	E	I	E	E	I	E	E	E	E	E	E	E
Sodium Benzoate	70	I	I	I	I	I	I	I	I	I	E	E	I
Sodium Bicarbonate	150	E	I	E	E	I	E	E	E	E	E	E	E
Sodium Bisulfate	150	E	I	E	E	I	E	E	E	E	E	E	E
Sodium Bisulfite	70	E	G	E	E	E	E	E	E	E	E	E	E
Sodium Borate	70	E	E	E	E	E	E	E	E	E	E	E	E
Sodium Carbonate	70	E	E	E	E	E	E	E	E	E	E	E	E
Sodium Chlorate	70	E	E	E	E	E	E	E	I	I	E	E	I
Sodium Chloride	70	E	E	E	E	E	E	E	E	E	E	E	E
Sodium Chromate	150	X	X	E	X	X	X	X	X	X	E	I	X
Sodium Cyanide	70	E	E	E	E	E	E	E	E	E	E	E	E
Sodium Dichromate	150	X	X	E	X	X	X	I	E	E	E	E	E
Sodium Diphosphate	70	E	E	E	I	G	I	E	I	I	I	I	I
Sodium Ethoxide	70	I	I	I	I	I	I	I	I	I	E	I	E
Sodium Ferricyanide	70	I	I	I	I	I	I	I	I	I	E	E	I
Sodium Fluoaluminate 10%	70	I	I	I	I	I	I	I	I	I	I	I	E
Sodium Fluoride	70	E	E	E	E	E	I	E	E	I	E	G	E
Sodium Hydrate	150	X	X	E	X	X	X	X	E	X	E	E	E
Sodium Hydrochlorite 20%	100	X	X	X	X	X	X	X	E	I	E	E	E
Sodium Hydrosulfide	70	I	I	I	I	I	I	I	I	I	I	I	I
Sodium Hydrosulfite	100	I	I	I	I	I	I	I	E	I	E	E	E
Sodium Hydroxide	70	E	E	E	E	G	E	G	E	G	E	E	E
Sodium Hydroxide 50%	150	X	X	E	X	X	X	X	E	X	E	E	I
Sodium Hypochlorite	100	X	X	X	X	X	X	X	X	C	E	G	G

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Terpineol	70	X	X	G	G	X	X	G	E	E	E	E	E
Terresstic	70	I	I	I	I	I	I	I	I	I	E	E	I
Tertiary Butly Alcohol	70	E	E	E	E	E	E	X	E	E	E	I	E
Tertiary Butly Catechol	70	E	E	E	E	E	E	E	E	E	E	I	E
Tertiary Butly Mercaptan	70	X	X	X	X	X	X	X	I	E	E	I	I
Tetra Chloride	70	I	I	I	I	I	I	I	I	I	I	I	E
Tetrabromoethane	70	X	X	X	X	X	X	X	I	E	I	I	I
Tetrabromomethane	70	X	X	X	X	X	I	X	I	E	E	I	I
Tetrabutyl Titanate	70	E	E	E	E	E	E	E	I	E	I	I	I
Tetrachlorobenzene	70	X	X	X	X	X	X	X	G	G	E	G	G
Tetrachloroethane	70	X	X	C	X	X	X	X	E	E	E	I	G
Tetrachloroethylene	70	X	X	X	X	X	X	X	E	E	E	I	E
Tetrachloromethane	70	X	X	X	X	X	X	X	G	E	E	G	E
Tetrachloronaphthalene	70	X	X	X	X	X	X	X	E	G	E	G	F
Tetradecanol	100	E	I	E	E	I	E	E	E	X	E	E	E
Tetraethylene Glycol	150	E	I	E	E	I	E	E	E	E	E	E	E
Tetraethyllead (TEL)	70	X	X	X	X	E	X	E	E	E	E	G	E
Tetrahydrofuran	70	I	I	I	I	I	I	I	I	I	E	I	G
Tetrahydrofuran (THF)	70	X	X	G	G	X	X	X	E	X	E	X	I
Tetrahydronaphthalene	70	X	X	X	X	X	X	X	E	E	E	I	E
Tetralin (Tetrahydronaphthalene)	70	X	X	X	X	X	X	X	E	E	E	X	E
Thionyl Chloride	70	X	X	X	C	X	X	X	I	G	E	I	I
Thiophene (Thiofuran)	70	X	X	C	X	X	I	X	I	C	E	I	I
Tin Chloride	100	E	I	E	I	I	I	I	E	I	E	E	E
Titanium Tetrachloride	70	X	X	X	X	X	X	G	I	E	E	X	E
Toluene	70	X	X	X	X	X	X	X	E	E	E	G	E
Toluene Diisocyanate	70	X	X	E	E	X	X	X	I	G	E	I	I
Toluidien	70	X	X	X	I	I	X	X	E	E	E	I	I
Toluidine	100	I	I	I	I	I	I	I	I	I	E	I	X
Toluol (Toluene)	70	X	X	X	X	X	X	X	E	E	E	I	E
Toxophene 12 %	70	I	I	I	I	I	I	I	I	I	E	I	E
Transformer Oil (Akarel Types)	70	I	I	I	I	I	I	G	I	I	E	G	E
Transformer Oil (Petroleum Type)	70	X	X	X	X	E	C	G	E	E	E	E	E
Transformer Oil (Petroleum)	70	I	I	I	I	I	I	G	E	I	E	I	E
Transmission Fluid -Automatic	70	X	X	X	X	G	C	E	E	E	E	E	E
Transmission Fluid -Type A	70	X	X	X	X	E	G	E	E	E	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Transmission Oil A	70	I	I	I	I	I	I	E	I	I	E	G	G
Triacetin	70	E	E	E	E	E	E	E	E	X	E	I	E
Triaryl Phosphate	70	X	X	E	E	X	X	X	I	E	I	I	I
Tributoxyethyl Phosphate	70	G	G	E	E	X	X	X	E	E	E	E	E
Tributyl Amine	70	I	I	I	I	I	I	I	I	I	E	I	E
Tributyl Mercaptan	100	X	X	E	X	X	X	X	E	I	E	E	E
Tributyl Phosphate	70	E	C	E	E	X	X	X	E	X	E	E	E
Trichloro Benzene	70	X	X	X	X	X	X	X	E	E	E	I	E
Trichloroacetic Acid	70	C	E	E	E	X	X	E	E	C	E	I	G
Trichloroethane	70	X	X	X	X	X	X	X	E	E	E	I	E
Trichloropropane	100	X	X	X	X	X	X	X	G	E	E	I	E
Trichoroethylene	70	X	X	X	X	X	X	X	E	E	E	E	G
Tricresyl Phosphate	70	C	E	E	C	G	X	X	E	E	E	E	E
Tridecanol	100	E	I	E	E	I	E	E	E	X	E	E	E
Triethanolamine (TEA)	70	E	F	E	E	E	E	E	E	X	E	E	E
Triethyl Aluminum	70	X	X	C	C	X	X	X	I	E	I	I	I
Triethyl Borane	70	X	X	C	C	X	X	X	I	E	E	I	I
Triethylene Glycol	70	E	E	E	I	I	E	E	E	E	E	I	E
Trinitrotoluene	70	X	X	X	X	E	E	X	I	E	E	I	I
Trioctyl Phosphate	70	X	X	E	E	X	X	X	I	G	I	I	I
Triphenyl Phosphate	70	X	X	G	I	I	G	X	E	G	E	I	E
Trisodium Phosphate (TSP)	70	E	E	E	E	E	E	E	E	E	E	I	E
Tung Oil	70	X	X	C	C	E	G	E	E	E	E	G	E
Turbine Oil	70	X	X	X	X	X	X	X	E	E	E	I	E
Turpentine	70	X	X	X	X	X	X	X	E	E	E	X	E
Tycol A Turbio 37, 50, 58 & 60	70	I	I	I	I	I	I	I	I	I	E	E	I
Tyco Avalon 50, 57, 60	70	I	I	I	I	I	I	I	I	I	E	E	I
Ucon Hydrolube Oils	70	I	I	I	I	I	I	I	I	I	E	I	E
Ucon Hydrolube 15CP, 200CP	70	I	I	I	I	I	I	I	I	I	E	E	I
Ucon Hydrolube 275CP,300CP,550CP	70	I	I	I	I	I	I	I	I	I	E	I	I
Ucon M1	70	I	I	I	I	I	I	I	I	I	E	E	I
Undecyl Alcohol (Undecanol)	70	E	E	E	I	I	E	E	E	E	E	I	E
Union Hydraulic Tractor Fluid	70	I	I	I	I	I	I	I	I	I	E	E	I
Unsymmetrical Dimethylhydrazine	70	E	E	E	E	E	E	E	I	X	I	I	I
Uran	70	I	I	I	I	I	I	I	I	I	I	I	E
Urea (Carbamide)	70	E	I	E	I	E	E	E	E	I	E	E	E

Chemical	Tube compounds												
	Temp °F	Natural Rubber (NR)	SBR	Butyl (IIR)	EPDM	Neoprene (CR)	Hypalon (CSM)	Nitrile (NBR)	Crosslinked Polyethylene (XLPE)	Flurocarbon (Viton/Fluorel)	Flurocarbon Plastic (Teflon/TFE/FEP)	Modified Cross-link	UHMWP
Urine	70	I	I	I	E	E	E	I	E	I	E	I	E
V.M. & P. Naptha	70	I	I	I	I	I	I	I	I	I	E	I	E
Valeric Acid	70	E	I	E	E	X	I	X	I	I	E	I	I
Varnish	70	X	X	X	X	X	X	X	E	E	E	G	E
Vegetable Oils	70	X	X	E	C	C	G	E	E	E	E	I	E
Versilube F-50	70	E	E	E	E	E	E	E	I	E	E	I	I
Vinegar (Diluted Acetic Acid)	70	G	G	G	G	F	E	C	E	E	E	E	E
Vinyl Acetate	70	X	X	E	I	X	E	X	E	X	E	E	E
Vinyl Benzene	70	X	X	X	X	X	X	X	E	E	E	I	E
Vinyl Chloride	70	C	C	G	X	X	X	X	E	E	E	G	E
Vinyl Ether	70	I	I	I	I	I	I	I	I	I	I	I	C
Vinyl Fluoride	70	I	I	I	I	I	I	I	I	I	E	E	E
Vinyl Toluene	100	X	X	X	X	X	X	X	X	E	E	I	E
Vinyl Trichloride	100	X	X	X	X	X	X	X	E	E	E	C	E
Vitrea Oils	70	I	I	I	I	I	I	I	I	I	E	E	E
Wagner 21B Brake Fluid	70	E	E	E	E	E	E	C	I	X	E	I	I
Water	70	E	E	E	E	E	E	E	E	E	E	E	E
Water (Brine)	70	E	E	E	E	E	E	E	E	E	E	E	E
Water (Deionized)	70	E	E	E	E	E	E	E	E	E	E	E	E
Water (Distilled)	70	E	E	E	E	E	E	E	E	E	E	E	E
Water (Potable)	70	E	E	E	E	E	E	E	E	E	E	E	E
Water Glycols	70	E	E	E	E	E	E	E	E	E	E	E	E
Water in Oil Emulsions	70	I	I	I	I	I	I	I	I	I	E	I	E
Wax (Petroleum)	70	X	X	X	X	E	G	E	E	E	E	I	E
Whiskey , Wines	70	E	E	E	E	E	E	E	E	E	E	G	E
White Oil	70	X	X	X	X	X	G	X	E	E	E	I	E
White Pine Oil	70	X	X	X	X	X	X	G	I	E	I	I	I
White Vitriol (Zinc Sulfate)	70	E	E	E	E	E	E	E	E	E	E	I	E
Wood Alcohol (Methyl Alcohol)	70	E	E	E	E	E	E	E	E	G	E	I	E
Wood Oil	70	X	X	X	X	F	C	E	E	E	E	E	E
Xylene	70	X	X	X	X	X	X	X	E	E	E	E	E
Xylidine (Dimethyl Aniline)	70	X	X	C	G	X	X	X	E	X	E	I	E
Xyolo (Xylene)	70	X	X	X	X	X	X	X	X	E	E	I	E
Zeolites	70	E	E	E	E	E	E	E	I	E	I	I	I
Zeric	70	I	I	I	I	I	I	I	I	I	E	E	I
Zinc Acetate	70	E	X	E	E	G	E	G	I	X	E	E	I

